
**Magnesium and magnesium alloys —
Returns — Requirements, classification
and acceptance**

*Magnésium et alliages de magnésium — Retours — Exigences,
classification et acceptation*

STANDARDSISO.COM : Click to view the full PDF of ISO 23079:2005



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 23079:2005

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 23079 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 5, *Magnesium and alloys of cast or wrought magnesium*.

STANDARDSISO.COM : Click to view the full PDF of ISO 23079:2005

Magnesium and magnesium alloys — Returns — Requirements, classification and acceptance

1 Scope

This International Standard specifies general requirements, classification and acceptance for the different classes of magnesium returns.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

coating

any surface layer except a natural oxide layer

EXAMPLES Oil, paint, metal coating.

2.2

contaminant

physical or chemical component of magnesium returns which, if not properly monitored and managed, negatively affects the quality of the returns as a raw material for certain applications or shows hazardous properties during certain operations

2.3

insert

component consisting of metal or other materials which may be moulded into position or put into a finished product or article

EXAMPLES Bearing, screw thread insert.

2.4

returns, pl

raw material, destined for trade and industry, mainly consisting of magnesium and/or magnesium alloys, resulting from the collection or recovery of

— metal that arises at various stages of fabrication, or

— products after use,

to be used for the production of wrought or cast alloys and for other production processes

2.5

turnings, pl

returns consisting of grains, chips, curls, flakes, etc. resulting from machining or other operations

3 Ordering information

The ordering information shall define the magnesium returns and should cover aspects such as the following, in order to achieve a transparent transaction:

- the number of this International Standard (ISO 23079);
- recycling classes, with reference to the relevant subclause of this International Standard (see Clause 5 and Annex A);
- condition of the returns, e.g. moisture and any contamination with other materials, size, physical characteristics of pieces or particles, whenever meaningful and if not covered by class definition (see Clause 7);
- gross mass;
- information about the origin of the returns;
- condition in which the returns shall be delivered (loose, baled, etc.);
- required chemical composition, if not otherwise specified;
- certification and control documents;
- shipment documents required by law;
- other requirement as agreed.

4 General requirements

4.1 General

Relevant characteristics of magnesium returns not specified in this International Standard shall be subject to agreement between the purchaser and the supplier. If returns might contain any hazardous contaminants, the purchaser shall be notified and his agreement to receive the returns shall be obtained before shipment.

4.2 Condition of returns

If not otherwise agreed or specified, the returns shall be supplied as bulk returns. The returns shall be correctly packed and labelled to ensure safe transportation.

4.3 Foreign materials

If not otherwise specified, the returns shall be free from foreign material, e.g. aluminium-based material.

4.4 Mass tolerances

If not otherwise agreed, the difference between the consigned quantity and the ordered quantity shall not exceed $\pm 5\%$.

4.5 Chemical composition

Returns classified by one alloy shall meet the requirements of chemical composition for that alloy. Returns classified by two or more alloys shall meet the chemical composition agreed between purchaser and the supplier.

5 Recycling classification (see also Annex A)

5.1 Solid returns with no inserts, no coating

5.1.1 Classified by one alloy

- a) Returns with low surface area and thickness ≥ 1 mm

EXAMPLES Rejected parts, biscuits and runners.

- b) Returns with high surface area and thickness < 1 mm

EXAMPLES Flashes, thin castings.

5.1.2 Classified by two or more alloys

- a) Returns with low surface area and thickness ≥ 1 mm

EXAMPLES Rejected parts, biscuits and runners.

- b) Returns with high surface area and thickness < 1 mm

EXAMPLES Flashes, thin castings.

5.2 Solid returns with inserts, no coating

5.2.1 Classified by one alloy (types of insert shall be specified if relevant)

- a) Returns with low surface area and thickness ≥ 1 mm

EXAMPLES Rejected parts, biscuits and runners.

- b) Returns with high surface area and thickness < 1 mm

EXAMPLES Flashes, thin castings.

5.2.2 Classified by two or more alloys (types of insert shall be specified if relevant)

- a) Returns with low surface area and thickness ≥ 1 mm

EXAMPLES Rejected parts, biscuits and runners.

- b) Returns with high surface area and thickness < 1 mm

EXAMPLES Flashes, thin castings.

5.3 Solid returns with coating

5.3.1 Classified by one alloy (types of coating and insert shall be specified if relevant)

- a) Without inserts
b) With insoluble inserts
c) With soluble inserts

5.3.2 Classified by two or more alloys (types of coating and insert shall be specified if relevant)

- a) Without inserts
- b) With insoluble inserts
- c) With soluble inserts

5.4 Post-consumer returns

5.4.1 Classified by one alloy

To be further specified if necessary with regard to inserts, coatings, surface contaminants, etc.

5.4.2 Classified by two or more alloys

To be further specified if necessary with regard to inserts, coatings, surface contaminants, etc.

5.5 Turnings

The following characteristics shall be specified:

- type of alloy;
- foreign material content (non-magnesium based alloys);
- wet, oily or dry;
- condition (compacted, non-compacted);
- maximum dust content.

5.6 Residues, dross, sludge, etc.

5.6.1 Without salt

5.6.2 With salt

6 Sampling and testing

Sampling and testing shall be agreed upon between purchaser and supplier.

7 Acceptance procedure

All magnesium returns delivered against a specific order shall be accepted with reservation until the classification at the purchaser's premises is accomplished. Any observation on the incoming shipment which indicates a non-compliance shall be notified by the purchaser as soon as possible.

The classification shall include:

- the control of the arrival date and times of the delivery;
- the control of mass;
- visual inspection during unloading.

The classification may include:

- the determination of moisture;
- the determination of total volatile substances;
- the determination of foreign material;
- the determination of the chemical composition.

8 Treatment of non-conformities

Deliveries of returns in dispute, for either quantity or quality, shall be kept at the disposal of the supplier for an agreed period, unless different agreements between supplier and purchaser are made.

STANDARDSISO.COM : Click to view the full PDF of ISO 23079:2005