
**Light metals and their alloys — Titanium
and titanium alloys — Classification and
terminology**

*Métaux légers et leurs alliages — Titane et alliages de titane —
Classification et terminologie*

STANDARDSISO.COM : Click to view the full PDF of ISO 28401:2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

The reproduction of the terms and definitions contained in this International Standard is permitted in teaching manuals, instruction booklets, technical publications and journals for strictly educational or implementation purposes. The conditions for such reproduction are: that no modifications are made to the terms and definitions; that such reproduction is not permitted for dictionaries or similar publications offered for sale; and that this International Standard is referenced as the source document.

With the sole exceptions noted above, no other part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Material	1
3 Specific terms and definitions	2
4 Unwrought products	2
5 Wrought products	2
6 Castings	5
7 Methods of processing and treatment	6
8 Surface condition	8
9 Applications	8
10 Abbreviations for titanium melting methods	9
11 Classification of titanium and titanium alloys	9
11.1 General	9
11.2 Unalloyed titanium	9
11.3 Titanium alloys	9
12 Titanium grades and compounds	10
12.1 Commercially pure titanium (CP titanium)	10
12.2 Corrosion-resistance-enhanced grades of CP titanium	10
12.3 Titanium-base intermetallic compounds	10
Annex A (normative) Dividing line between titanium and titanium alloys	11
Annex B (normative) Explanatory notes concerning the definitions of wrought products	12
Alphabetical index	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 28401 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 11, *Titanium*.

STANDARDSISO.COM : Click to view the full PDF of ISO 28401:2010

Light metals and their alloys — Titanium and titanium alloys — Classification and terminology

1 Scope

This International Standard gives a classification of titanium and titanium alloys. It also gives terms and definitions in the field of titanium and its alloys.

2 Material

2.1

titanium sponge

products of metallic titanium in porous and sponge-like form, which is applied as titanium metal melting stock

NOTE The oxidized titanium ore is first chlorinated to tetrachloride and is condensed and purified and then reduced with magnesium or sodium under the inert atmosphere to produce titanium sponge.

2.2

alloy

metallic substance consisting of a mixture of the basic metallic element (the element predomination by mass) and other elements, such as alloying elements and impurities

2.3

alloying element

metallic or non-metallic elements intentionally added to, or retained by, basic metal for the purpose of giving that metal certain special properties

2.4

impurity

metallic or non-metallic elements present but which are not intentionally added to, or retained by, a metal

2.5

wrought alloy

alloy primarily intended for the production of wrought products by hot and/or cold plastic forming

2.6

casting alloy

alloy primarily intended for the production of castings

2.7

master alloy

alloy intended only for addition to a melt to adjust composition or to control impurities

2.8

heat-treatable alloy

alloy capable of being strengthened by a suitable thermal treatment

2.9

non-heat-treatable alloy

alloy strengthened by cold working only and incapable of being substantially strengthened by thermal treatment

3 Specific terms and definitions

3.1

intermediate-strength alloys

alloys with improved properties due to a limited percentage of alloying elements enhancing mechanical resistance and, from case to case, also corrosion resistance

3.2

high-strength standard alloys

alloys with properties similar to the alloy work-horse Ti-6Al-4V (Al $\approx$ 6 %, V $\approx$ 4 %), well defined and used with experience

3.3

special alloy grades

high-strength and highly alloyed grades for special use, for example, in military and space equipment

4 Unwrought products

4.1

unwrought product

general term for products obtained by melting or casting processes

EXAMPLES Ingots for rolling, ingots for extruding, ingots for forging and ingots for remelting.

4.2

electrode for remelting

formed from titanium sponge and alloying elements or consolidated from recycled and processed scrap, normally to be remelted finally at least once under a vacuum or in argon

4.3

ingot for rolling

titanium ingot in a form suitable for rolling, melted by EB, VAR, VASM or PM methods applied for at least the final cycle under a vacuum or in argon

4.4

ingot for extruding

titanium ingot in a form suitable for extrusion of bars, tubes and slabs melted by EB, VAR, VASM or PM methods applied for at least the final cycle under a vacuum or in argon

4.5

ingot for forging

titanium ingot in a form suitable for forging, melted by EB, VAR, VASM or PM methods applied for at least the final cycle under a vacuum or in argon

4.6

ingot for remelting

titanium ingot in a form suitable for remelting after having been processed metallurgically for composition, melted by EB, VAR, VASM or PM methods applied for at least the final cycle under a vacuum or in argon

5 Wrought products

5.1

wrought product

general term for products obtained by hot and/or cold plastic deformation processes, such as extruding, forging, hot rolling, cold rolling or drawing, either solely or in combination

EXAMPLES Rod/bar, billets, wire, tube, shape/profile, sheet, plate, strip, foils, die forgings, open die forgings.

NOTE For the classification principles of wrought products, see Annex B.

5.2

billets

solid wrought product of uniform cross-section that is above 10 000 mm² along its whole length, supplied in straight lengths

NOTE The cross-sections are in the shape of circles, ovals, squares, rectangles, equilateral triangles or regular polygons. Products with a square, rectangular, triangular or polygonal cross-section may have corners rounded along their whole length.

5.3

rod/bar

solid wrought product of uniform cross-section that is under 10 000 mm² along its whole length, supplied in straight lengths

NOTE 1 The cross-sections are in the shape of circles, ovals, squares, rectangles, equilateral triangles or regular polygons. Products with a square, rectangular, triangular or polygonal cross-section may have corners rounded along their whole length.

NOTE 2 For rectangular bars:

- the thickness exceeds one-third of the width;
- the term “rectangular bar” includes “flattened circles” and “modified rectangles”, of which two opposite sides are convex arcs, the other two sides being straight, of equal length and parallel.

5.4

wire

solid wrought product of uniform cross-section along its whole length, supplied in coiled form

NOTE 1 The cross-sections are in the shape of circles, ovals, squares, rectangles, equilateral triangles or regular polygons. Products with a square, rectangular, triangular, or polygonal cross-section may have corners rounded along their whole length.

NOTE 2 For rectangular wires:

- the thickness exceeds one-third of the width;
- the term “rectangular wire” includes “flattened circles” and “modified rectangles”, of which two opposite sides are convex arcs, the other two sides being straight, of equal length and parallel.

5.5

drawing stock

intermediate solid wrought product of uniform cross-section along its whole length supplied in coils

NOTE The cross-sections are approximately round, triangular or regular polygonal with dimensions usually exceeding 5 mm.

5.6

tube

hollow wrought product of uniform cross-section with only one enclosed hollow space along its whole length, and with a uniform wall thickness, supplied in straight lengths or in coiled form

NOTE 1 The cross-sections are in the shape of circles, ovals, squares, rectangles, equilateral triangles or regular polygons. Hollow products with square, rectangular, equilateral triangular or regular polygonal cross-sections, which may have corners rounded along their whole length, are also to be considered as tubes, provided the inner and outer peripheries are concentric and have the same form and orientation.

NOTE 2 Tubes can also be formed by piercing trespassing and by forming and joining sheet or strip.

NOTE 3 Bent, threaded, drilled, waisted, expanded and cone-shaped hollow products in this form, when derived from tubes as defined above, are classified as tubes.

5.7

profile/shape

wrought product of uniform cross-section along its whole length, with a cross-section other than rod/bar, wire, tube, sheet, plate or strip, supplied in straight lengths or in coiled form

NOTE According to the form of its cross-section, it is called hollow profile or non-hollow profile.

a) Hollow profile

The cross-section includes:

- either one enclosed hollow space, provided that the cross-section is for other than a tube, or
- more than one enclosed hollow space.

b) Non-hollow profile

The cross-section does not include any enclosed hollow space.

5.8

plate

flat-rolled product of rectangular cross-section with uniform thickness over 5 mm, supplied in straight lengths (i.e. flat) usually with sheared, sawn or flame-cut/plasma-cut edges or water-jet cutting

NOTE The thickness does not exceed one-tenth of the width.

5.9

sheet

flat-rolled product of rectangular cross-section with uniform thickness over 0,20 mm and up to and including 5 mm, supplied in straight lengths (i.e. flat) usually with sheared or sawn edges or water jet cutting

NOTE The thickness does not exceed one-tenth of the width.

5.10

strip

flat-rolled product of rectangular cross-section with uniform thickness over 0,20 mm, supplied in coils usually with slit edges

NOTE 1 The thickness does not exceed one-tenth of the width.

NOTE 2 Corrugated, embossed (with patterns, for example, grooves, ribs, checkers, tears, buttons, lozenges), coated, edge conditioned and perforated products in this general form when derived from strip as defined above are classified as strip.

NOTE 3 In some English-speaking countries, "strip" is called "coiled sheet".

5.11

foil

flat-rolled product of rectangular cross-section with uniform thickness equal to or less than 0,20 mm

NOTE In some countries, the term "foil" covers two different products:

- foil: products with lesser thickness;
- thin strip: products with greater thickness.

The dimensional limitations between these two products may vary from country to country.

5.12

forging stock

hot-worked intermediate solid wrought product, for example rod/bar or billets, or any other cross-section, suitable for forging

NOTE Forging stock may also be a cast product, for example, ingot for forging (see 4.5).

5.13**casting stock**

cast or hot-worked intermediate solid wrought product, for example, rod/bar or billets, or any other cross-section, suitable for casting

5.14**forging**

wrought product formed by hammering or pressing, usually when hot, between open dies (hand forging) or closed dies (drop or die forging)

5.15**blank**

piece of titanium of regular or irregular shape taken from a flat wrought product intended for subsequent processing, such as bending, stamping or deep drawing

5.16**circle**

circular blank

6 Castings**6.1****casting**

general term for products at or near the finished shape, formed by solidification of titanium or titanium alloys in a mould

6.2**sand/graphite casting**

rammed graphite moulding
casting formed in a sand/graphite mould

6.3**permanent mould casting****chill casting**

casting formed in a metal mould, the molten metal being introduced by gravity or low-pressure feed

6.4**pressure die casting****die casting**

casting formed in a metal mould, the molten metal being introduced under high pressure

6.5**centrifugal casting**

casting formed by centrifugal force in a rotating mould, the major axis of the casting coinciding with the axis of rotation, and the thickness of the casting being determined by the dimensions of the mould and quantity of titanium poured

NOTE Centrifugal casting is not to be confused with casting under centrifugal pressure.

6.6**investment casting**

casting method using ceramic shells inert to molten titanium

NOTE The wax pattern has to be removed before pouring the liquid metal into the mould.

6.7

skull melting technique

technique where the molten metal is contained in a water-cooled copper crucible while confined in a vacuum chamber

NOTE The reactive liquid titanium is prevented from dissolving the crucible due to a solid frozen titanium skull.

6.8

hot isostatic pressing

HIP

post-moulding process to densifying castings under temperatures and pressures in an inert atmosphere

7 Methods of processing and treatment

7.1

alpha-beta processing

hot working (forging/rolling/annealing) in a temperature field below the beta-transus temperature, usually the final hot-working temperature range

7.2

annealing

thermal treatment to soften metal by removal of strain hardening resulting from cold or hot working by recrystallization or recovery

7.3

ageing

precipitation heat treatment

thermal treatment of an alloy at above room temperature for strengthening by precipitation of soluble constituents from the super-saturated solid solution

7.4

beta processing

hot working (forging/rolling/annealing) in a temperature field above the beta-transus temperature

7.5

beta-transus temperature

temperature above which no alpha phase (hexagonal closed packed crystal configuration) exists

7.6

bright annealing

thermal treatment in a controlled atmosphere to prevent scaling or oxidation during annealing

7.7

cold working

plastic deformation of titanium or alloy at a temperature such that strain hardening occurs

7.8

descaling

procedure to remove the layer of oxide formed on the surface during heating by sand blasting or molten salt bath followed by pickling

NOTE Shot blasting with steel grit or sand is used for thick-walled cross-sections. A molten salt bath containing aqueous solution is used for thin-walled pieces, and especially for coils.

— molten salt bath: aqueous solution for thin-walled pieces, especially for coils.

7.9**diffusion soaking**

process in which a metal or an alloy is heated for a period at high temperature, in particular to eliminate or relieve chemical micro-segregation by diffusion

7.10**homogenizing**

process in which a metal or an alloy is heated for a period at a high temperature, in particular to make the structure uniform at a controlled level

7.11**hot working**

plastic deformation of titanium or alloy within a temperature range such that strain hardening does not occur

7.12**partial annealing**

thermal treatment of cold-worked titanium or alloy to reduce the strength properties to a controlled level

7.13**pickling**

procedure to remove the oxygen-rich layer in an aqueous solution followed by shot-blasting for thin-walled pieces

NOTE Prevention against hydrogen pick-up is necessary.

7.14**quenching**

process of cooling a metal or alloy from an elevated temperature by contact with a solid, a liquid or a gas at a rate rapid enough to retain one or all of the soluble constituents in solid solution

NOTE Common media used are water, oil or a similar product, or accelerated air.

7.15**skin passing**

final light cold-rolling pass on polished rolls giving a bright finish on coils of commercially pure titanium grades with a controlled influence on the mechanical properties

7.16**solution heat treatment**

process in which an alloy is heated to a suitable temperature and is held at this temperature long enough to allow soluble constituents to enter into solid solution where they are retained in a super-saturated state after quenching

7.17**solution heat treated and aged****STA**

solution heat treatment followed by artificial ageing (precipitation heat treatment)

7.18**stabilizing**

thermal treatment used to promote stability under service conditions in, for example, dimensions, mechanical properties, structure or internal stress

7.19**strain hardening**

modification of a titanium structure by cold working, resulting in an increase in strength and hardness, generally with some loss of ductility

7.20

stress relieving

annealing method for reducing internal stress by moderate temperatures and controlled smooth cooling

7.21

stretch levelling

procedure for smoothing the features of coils by stretching and bending of commercially pure titanium grades with a controlled influence to the mechanical properties

7.22

superplastic forming

SPF

forming method using superplasticity which is confirmed in several practical alloys including $\alpha + \beta$ titanium alloys and occurs at a high temperature and low strain rate

NOTE The elongation of these alloys during tensile testing attains several hundred percent.

7.23

upset forging

process of breaking down a cast ingot in the beta-field to control the conversion rate and/or to enlarge an ingot in the transverse direction

8 Surface condition

8.1

alpha case

oxygen-, nitrogen- and/or carbon-enriched alpha-stabilized surface layer resulting from elevated-temperature exposure

NOTE Because it has a high hardness with poor ductility, it is commonly removed by pickling or mechanical means.

8.2

surface finish

condition of finishing surface of titanium products

NOTE The typical finishing surfaces are pickled dull surface, vacuum-annealed bright surface and shot-blasted surface.

8.3

surface treatment

surface treatment for achieving special properties

NOTE The special surface treatments are as follows:

- a) surface treatment for improving corrosion resistance with oxidizing, coating by precious metals and nitriding;
- b) surface treatment for improving wear resistance with metallic plating, thermal spraying, oxidizing and deposit welding;
- c) surface treatment for design with polishing and anodic oxidation;
- d) surface treatment for improving surface conductivity with metal plating by Ni or Cu.

9 Applications

9.1

commercial applications

generally commercialized use, except aerospace, military and special use

9.2

non-aerospace applications

industrial, military and special use, except aerospace use

10 Abbreviations for titanium melting methods

EB	<u>E</u> lectron <u>B</u> eam (re)melting
VAR	<u>V</u> acuum <u>A</u> rc <u>R</u> emelting
VASM	<u>V</u> acuum <u>A</u> rc <u>S</u> kull <u>M</u> elting
PM	<u>P</u> lasma <u>M</u> elting

11 Classification of titanium and titanium alloys

11.1 General

Titanium and titanium alloys are classified as follows (for further details, see Annex A)

11.2 Unalloyed titanium

Unalloyed titanium is metal with a minimum mass fraction of 98,5 % of titanium, provided that, unless otherwise specified, the mass fraction of any residual element does not exceed the limit specified in Table 1.

Table 1 — Limits

Each residual element	$\leq 0,1 \%$
Total residual elements	$\leq 0,4 \%$

Exceptions exist in the case of elements added in small quantities for the purpose of enhancing the corrosion resistance but not substantially enhancing the mechanical properties.

Those elements are, for example, palladium, ruthenium, nickel, molybdenum, cobalt, chromium or mixtures of some of these elements.

The mass fraction of elements other than those specified in Table 2 shall not exceed 1 %.

**Table 2 — Maximum mass fraction of non-titanium elements
for the purpose of corrosion-resistance enhancement
in the case of commercially pure titanium grades**

Pd	0,25 %
Ru	0,14 %
Ni	0,9 %
Co	0,8 %
Cr	0,2 %
Mo	0,4 %

11.3 Titanium alloys

Titanium alloys are metallic substances in which titanium predominates, by mass, over each of the other elements, provided that

- the mass fraction of at least one of the elements is greater than the limit specified in Table 2, or
- the mass fraction of the other elements exceeds 1 %.

12 Titanium grades and compounds

12.1 Commercially pure titanium (CP titanium)

The principal difference among these grades is the levels of interstitial elements and iron. Increasing levels of these elements lead to higher strength, but lower ductility.

12.2 Corrosion-resistance-enhanced grades of CP titanium

The grades with enhanced corrosion resistance are obtained by adding low percentages of palladium, ruthenium, nickel, molybdenum, cobalt and chromium, either singly or in combination, with the limits according to Table 2. The mechanical behaviour is comparable to the standard commercially pure (CP) grades.

12.3 Titanium-base intermetallic compounds

These alloys (metal-to-metal compound) are formed by more than two metallic elements having the crystal structure of an ordered lattice. Different crystal structures from the constituent metallic elements and in the atomic bonding, covalent bonding and/or ionic bonding state are added to the basic metallic bonding. Completely different crystal structures and/or properties originate from the conventional alloy (solid solution). TiAl and Ti₃Al are fundamental titanium base intermetallic compounds and show excellent mechanical properties at high temperatures.

STANDARDSISO.COM : Click to view the full PDF of ISO 28401:2010