
**Plastics hoses — Textile-reinforced types
for compressed-air applications —
Specification**

*Tuyaux en plastique — Types armés de textile pour applications avec
de l'air comprimé — Spécifications*

STANDARDSISO.COM : Click to view the full PDF of ISO 5774:2006



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 5774:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Classification.....	2
5 Couplings and end fittings	2
6 Materials and construction	2
7 Dimensions and tolerances	2
7.1 Inside diameter, tolerances and minimum wall thickness	2
7.2 Concentricity	3
7.3 Tolerances on length.....	3
8 Physical properties.....	4
8.1 Plastic compounds	4
8.1.1 Tensile strength and elongation at break of lining and cover	4
8.1.2 Resistance to ageing	4
8.1.3 Loss in mass on heating	4
8.1.4 Resistance to liquids	4
8.1.5 Hydrolysis test	4
8.2 Performance requirements on finished hoses	5
8.2.1 Hydrostatic requirements	5
8.2.2 Adhesion.....	5
8.2.3 Exposure to a xenon arc lamp.....	5
8.2.4 Bending test	6
8.2.5 Low-temperature flexibility	6
9 Frequency of testing.....	6
10 Marking	7
11 Recommendations for packaging and storage	7
12 Test report	7
Annex A (normative) Hydrolysis test	8
Annex B (normative) Type approval and routine tests	10
Annex C (informative) Production acceptance tests	11
Annex D (informative) Couplings and end fittings.....	12
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5774 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This third edition cancels and replaces the second edition (ISO 5774:1997), which has been technically revised.

Introduction

This International Standard has been prepared to provide minimum acceptable requirements for the satisfactory performance of flexible thermoplastics hoses, textile reinforced, for compressed-air applications.

Maximum working pressures of each hose type are specified with two operating temperatures.

Some hose materials will require a hydrolysis test (given in Annex A).

STANDARDSISO.COM : Click to view the full PDF of ISO 5774:2006

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 5774:2006

Plastics hoses — Textile-reinforced types for compressed-air applications — Specification

1 Scope

This International Standard specifies the requirements for four types of flexible thermoplastic hose, textile reinforced, for compressed-air applications in the temperature range from $-10\text{ }^{\circ}\text{C}$ to $+60\text{ }^{\circ}\text{C}$.

The four types are classified as light service for a maximum working pressure of 7 bar at $23\text{ }^{\circ}\text{C}$ and 4,5 bar at $60\text{ }^{\circ}\text{C}$, medium service for a maximum working pressure of 10 bar at $23\text{ }^{\circ}\text{C}$ and 6,5 bar at $60\text{ }^{\circ}\text{C}$, heavy service for a maximum working pressure of 16 bar at $23\text{ }^{\circ}\text{C}$ and 11 bar at $60\text{ }^{\circ}\text{C}$, and heavy service for use in mining for a maximum working pressure of 25 bar at $23\text{ }^{\circ}\text{C}$ and 13 bar at $60\text{ }^{\circ}\text{C}$.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scales for assessing change in colour*

ISO 176:2005, *Plastics — Determination of loss of plasticizers — Activated carbon method*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1307, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1746, *Rubber or plastics hoses and tubing — Bending tests*

ISO 1817, *Rubber, vulcanized — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of dimensions*

ISO 4672:1997, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guide to selection, storage, use and maintenance*

ISO 11758:1995, *Rubber and plastics hoses — Exposure to a xenon arc lamp — Determination of changes in colour and appearance*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

4 Classification

Hoses are designated as one of the following four types depending on their pressure rating at the specified temperature:

Type A: General industrial use — light service — for a maximum working pressure of 7 bar at 23 °C and 4,5 bar at 60 °C.

Type B: General industrial use — medium service — for a maximum working pressure of 10 bar at 23 °C and 6,5 bar at 60 °C.

Type C: Heavy service — for a maximum working pressure of 16 bar at 23 °C and 11 bar at 60 °C.

Type D: Heavy service — for use in mining and outdoor work — for a maximum working pressure of 25 bar at 23 °C and 13 bar at 60 °C.

The hoses are not intended for the transport of oil. However, compressed air coming from a compressor may contain some oil in suspension.

5 Couplings and end fittings

Hoses may be fitted with the appropriate coupling type and end fitting to form hose assemblies.

NOTE Guidance on coupling type is given in Annex D and ISO/TR 17784.

6 Materials and construction

The hoses shall consist of:

- a) a lining made of a flexible thermoplastics material;
- b) a reinforcement made of a natural or synthetic textile material applied by any suitable technique;
- c) a cover made of a flexible thermoplastics material.

The lining and the cover shall be of uniform thickness, concentric, fully gelled and free from visible cracks, porosity, foreign inclusions and any other defects which could cause the hose to be unserviceable.

7 Dimensions and tolerances

7.1 Inside diameter, tolerances and minimum wall thickness

When measured in accordance with ISO 4671, the inside diameter of hoses shall lie within the tolerance limits given in Table 1 and the wall thickness shall meet the minimum requirement given in the table.

Table 1 — Nominal bores, inside diameters, tolerances and minimum wall thicknesses

Nominal bore	Inside diameter mm	Tolerance mm	Minimum wall thickness mm			
			Type A	Type B	Type C	Type D
4	4	$\pm 0,25$	1,5	1,5	1,5	2,0
5	5	$\pm 0,25$	1,5	1,5	1,5	2,0
6,3	6,3	$\pm 0,25$	1,5	1,5	1,5	2,3
8	8	$\pm 0,25$	1,5	1,5	1,5	2,3
9	8,5	$\pm 0,25$	1,5	1,5	1,5	2,3
10	9,5	$\pm 0,35$	1,5	1,5	1,8	2,3
12,5	12,5	$\pm 0,35$	2,0	2,0	2,3	2,8
16	16	$\pm 0,5$	2,4	2,4	2,8	3,0
19	19	$\pm 0,7$	2,4	2,4	2,8	3,5
25	25	$\pm 1,2$	2,7	3,0	3,3	4,0
31,5	31,5	$\pm 1,2$	3,0	3,3	3,5	4,5
38	38	$\pm 1,2$	3,0	3,5	3,8	4,5
40	40	$\pm 1,5$	3,3	3,5	4,1	5,0
50	50	$\pm 1,5$	3,5	3,8	4,5	5,0

7.2 Concentricity

When determined in accordance with ISO 4671, the concentricity, based on the difference in indicator reading between the inside surface of the lining and the outside surface of the cover, shall be no greater than 0,3 mm for hoses of minimum wall thickness from 1,5 mm up to and including 3,0 mm, no greater than 10 % of the wall thickness for hoses of minimum wall thickness over 3,0 mm and up to and including 5,0 mm, and no greater than 15 % of the wall thickness for hoses of minimum wall thickness over 5,0 mm as given in Table 2.

Table 2 — Concentricity

Minimum wall thickness mm	Concentricity
1,5 to 3,0	$\leq 0,3$ mm
over 3,0 to 5,0	≤ 10 % of wall thickness
over 5,0	≤ 15 % of wall thickness

7.3 Tolerances on length

The tolerances on cut lengths of hose shall be in accordance with ISO 1307.

8 Physical properties

8.1 Plastic compounds

8.1.1 Tensile strength and elongation at break of lining and cover

When determined in accordance with ISO 37, the tensile strength and elongation at break shall not be less than the values given in Table 3.

Table 3 — Tensile strength and elongation at break

Hose component	Minimum tensile strength MPa	Minimum elongation at break %
Lining	15,0	250
Cover	15,0	250

Testing shall be carried out either on test pieces taken from the hose wall or on test pieces taken from a sheet of hose material made using a laboratory press.

8.1.2 Resistance to ageing

After ageing for 7 days at a temperature of $(70 \pm 2) ^\circ\text{C}$, as specified in ISO 188, the tensile strength and elongation at break of the lining and cover, as determined by ISO 37, shall not vary by more than the values given in Table 4 in comparison with the values of these properties before ageing.

Table 4 — Change in tensile strength and elongation from original value

Hose component	Change in tensile strength from original value %	Change in elongation at break from original value %
Lining	15	25
Cover	15	25

8.1.3 Loss in mass on heating

When tested in accordance with method B of ISO 176:2005, the materials of the lining and cover shall have a loss in mass not greater than 2 %.

8.1.4 Resistance to liquids

After immersion in oil No. 1 as described in ISO 1817 at $(60 \pm 1) ^\circ\text{C}$ for 72 h, the volume of a test piece shall not vary by more than 15 %.

8.1.5 Hydrolysis test

When materials are used in the lining and/or cover that are susceptible to hydrolysis, a hydrolysis test shall be carried out, using the method specified in Annex A, either on ISO 37 dumb-bell test pieces taken from the hose wall or on ISO 37 dumb-bell test pieces taken from a sheet of material made using a laboratory press.

After exposure to $(95 \pm 5) \%$ relative humidity at $(80 \pm 2) ^\circ\text{C}$ for 500 h, neither the lining nor the cover shall show visible evidence of cracking, porosity or other defects.

The values of the tensile strength and the elongation at break of the ISO 37 dumb-bell test pieces after the hydrolysis test shall be more than 40 % of the original values.

8.2 Performance requirements on finished hoses

8.2.1 Hydrostatic requirements

When tested in accordance with ISO 1402, hoses shall meet the requirements specified in Table 5.

Table 5 — Hydrostatic pressure requirements at 23 °C and 60 °C

Hose type	Maximum working pressure bar ^a		Proof pressure bar ^a	Minimum burst pressure bar ^a		Change in dimensions at proof pressure 23 °C	
	23 °C	60 °C	23 °C	23 °C	60 °C	Length %	Diameter %
A	7	4,5	14	28	18	± 8	± 10
B	10	6,5	20	40	26	± 8	± 10
C	16	11	32	64	45	± 8	± 10
D	25	13	50	100	50	± 8	± 10

^a 1 bar = 0,1 MPa

During and after the proof pressure test, the hose shall be examined for evidence of leakage, cracking, abrupt distortion (indicating an irregularity in the construction) or any other faults. No such defects shall be observed.

8.2.2 Adhesion

When determined in accordance with ISO 8033, the adhesion between the lining and the cover shall not be less than 2,0 kN/m.

Use type 1 test pieces for hoses of inside diameter up to 32 mm, and type 2 test pieces for hoses of inside diameter of 38 mm and above.

8.2.3 Exposure to a xenon arc lamp

When tested in accordance with ISO 11758, preferably without water spray (see below), the cover shall show no evidence of cracking. Any change in colour caused by the exposure shall be determined by comparing the exposed test pieces with unexposed test pieces using the grey scale (see ISO 105-A02). The grey-scale rating thus determined shall be more than 3.

Testing without spraying is recommended. By agreement between the interested parties, however, testing with spraying may be carried out (see ISO 11758:1995, Annex B).

8.2.4 Bending test

When bent to the minimum bend radius given in Table 6, in accordance with one of the methods specified in ISO 1746 (use the method most appropriate to the size of hose), hoses shall show no evidence, under visual examination, of kinking, breaking or peeling. The value of the coefficient of deformation (*T/D*) shall not be lower than 0,8.

Table 6 — Minimum bend radius

Nominal bore	Minimum bend radius mm
4	24
5	30
6,3	40
8	50
9	55
10	60
12,5	75
16	96
19	115
25	175
31,5	220
38	310
40	320
50	400

8.2.5 Low-temperature flexibility

When tested at $(-10 \pm 2) ^\circ\text{C}$ in accordance with method B of ISO 4672:1997, hoses shall be capable of being bent around a mandrel having an outside diameter equal to twice the minimum bend radius specified in 8.2.4.

No cracks shall be detected and the hose shall subsequently pass the proof pressure test in 8.2.1.

9 Frequency of testing

Type approval and routine testing shall be as specified in Annex B.

Type approval tests are those tests required to confirm that a particular hose design, manufactured by a particular method, meets all the requirements of this International Standard. The tests shall be repeated at a maximum of five-year intervals, or whenever a change in the method of manufacture or materials used occurs. They shall be performed on all sizes, and on all classes and types except those of the same size and construction.

Routine tests are those tests required to be carried out on each length of finished hose prior to dispatch.

Production acceptance tests are those tests, specified in Annex C, which should preferably be carried out to control the quality of manufacture. The frequencies specified in Annex C are given as a guide only.

10 Marking

Hoses shall be continuously and durably marked with the following minimum information:

- a) the manufacturer's name or trademark;
- b) the number and year of publication of this International Standard;
- c) the hose type;
- d) the nominal bore;
- e) the maximum working pressure;
- f) the quarter and the year of manufacture.

EXAMPLE MAN/ISO 5774:2006/TYPE A/10,7 bar@23 °C/4,5 bar@60 °C/3Q06

11 Recommendations for packaging and storage

These are given in ISO 8331.

12 Test report

If requested by the purchaser, a test report shall be supplied by the hose manufacturer or supplier.

Annex A (normative)

Hydrolysis test

A.1 General

This test determines the susceptibility of hose materials to degradation due to the absorption of water at high temperatures and humidities.

NOTE 1 The test may be carried out using, in addition, reference test pieces taken from the hose wall and/or from a sheet of TPU (thermoplastic polyurethane) or PA (polyamide).

NOTE 2 It is preferable that any metal clips on the test piece holders in the exposure chamber be covered with aluminium foil or a polytetrafluoroethylene coating or protected in some other way so that they do not contact the test pieces directly.

A.2 Procedure

A.2.1 Tests on plastic compounds

In the case of compounds, prepare a sufficient number of ISO 37 dumb-bell test pieces using a laboratory press.

Prior to hydrolysis testing, dry the test pieces for 2 h in a circulating-air oven at $(100 \pm 2) ^\circ\text{C}$. After drying, remove the test pieces from the oven and allow them to cool to $(23 \pm 2) ^\circ\text{C}$ in a desiccator.

Using half of the test pieces, measure, in accordance with ISO 37, the original values of the tensile strength and the elongation at break.

Expose the remaining test pieces to $(95 \pm 5) \%$ relative humidity for 500 h at $(80 \pm 2) ^\circ\text{C}$ (the use of a thermostatically controlled environmental test chamber is recommended).

Following exposure, remove the test pieces from the chamber and carry out a visual examination (see A.3.1).

Condition the exposed test pieces in the desiccator for 24 h at $(23 \pm 2) ^\circ\text{C}$ to allow all traces of moisture to disappear.

Measure, in accordance with ISO 37, the tensile strength and the elongation at break of the exposed test pieces.

A.2.2 Tests on finished hoses

In the case of finished hoses, prepare ten ISO 37 dumb-bell test pieces, each at least 150 mm in length.

Prior to hydrolysis testing, dry the test pieces for 2 h in a circulating-air oven at $(100 \pm 2) ^\circ\text{C}$. After drying, remove the test pieces from the oven and allow them to cool to $(23 \pm 2) ^\circ\text{C}$ in a desiccator.

Using five of the test pieces, measure, in accordance with ISO 37, the original values of the tensile strength and the elongation at break.

Expose the remaining five test pieces to (95 ± 5) % relative humidity for 500 h at (80 ± 2) °C (the use of a thermostatically controlled environmental test chamber is recommended).

Following exposure, remove the test pieces from the chamber and carry out a visual examination (see A.3.2).

Condition the exposed test pieces in the desiccator for 24 h at (23 ± 2) °C to allow all traces of moisture to disappear.

Measure, in accordance with ISO 37, the tensile strength and the elongation at break of the exposed test pieces.

A.3 Assessment

A.3.1 Tests on plastic compounds

Examination of the exposed test pieces shall not reveal any visible signs of cracking, porosity or other defects. The values of the tensile strength and elongation at break measured after exposure shall be more than 40 % of the original values.

A.3.2 Tests on finished hoses

Examination of the exposed test pieces shall not reveal any visible signs of cracking, porosity or other defects in the lining and/or cover. The values of the tensile strength and elongation at break measured after exposure shall be more than 40 % of the original values.

Annex B (normative)

Type approval and routine tests

Table B.1 gives the tests to be carried out for type approval and routine testing as defined in Clause 9.

Table B.1

Dimension/property under test (with reference to relevant subclause)	Type approval testing	Routine testing
Inside diameter/tolerances/minimum wall thickness (7.1)	X ^a	X
Concentricity (7.2)	X	X
Tolerances on length (7.3)	X	X
Tensile strength and elongation at break of lining and cover (8.1.1)	X	N.A. ^b
Resistance to ageing (8.1.2)	X	N.A.
Loss in mass on heating (8.1.3)	X	N.A.
Resistance to liquids (8.1.4)	X	N.A.
Hydrolysis test (8.1.5)	X	N.A.
Proof pressure (8.2.1)	X	N.A.
Burst pressure at 23 °C and 60 °C (8.2.1)	X	N.A.
Change in length and diameter at proof pressure (8.2.1)	X	N.A.
Adhesion (8.2.2)	X	N.A.
Exposure to xenon arc lamp (8.2.3)	X	N.A.
Bending test (8.2.4)	X	N.A.
Low-temperature flexibility (8.2.5)	X	N.A.
^a X = Test required. ^b N.A. = Not applicable.		