
Coke — Determination of total moisture

Coke — Détermination de l'humidité totale

STANDARDSISO.COM : Click to view the full PDF of ISO 579:2013



STANDARDSISO.COM : Click to view the full PDF of ISO 579:2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Sample	1
6 Procedure	1
7 Expression of results	2
7.1 Sample as analysed (see Clause 6)	2
7.2 Visibly wet sample (see Clause 5)	2
8 Precision	2
8.1 Repeatability limit	2
8.2 Reproducibility limit	3
9 Test report	3

STANDARDSISO.COM : Click to view the full PDF of ISO 579:2013

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 579 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This fourth edition cancels and replaces the third edition (ISO 579:1999), which has been technically revised.

STANDARDSISO.COM : Click to view the full PDF of ISO 579:2013

Coke — Determination of total moisture

1 Scope

This International Standard specifies a method for determining the total moisture of coke. It can be used for the determination of moisture of blast-furnace coke, foundry coke and other high-temperature carbonization products.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13909-6, *Hard coal and coke — Mechanical sampling — Part 6: Coke — Preparation of test samples*

3 Principle

A sample is heated in air at 120 °C to 200 °C and maintained at this temperature until constant in mass. The moisture percentage is calculated from the loss in mass of the sample. Coke is not liable to oxidation under the specified conditions.

4 Apparatus

4.1 Drying oven, capable of maintaining a substantially uniform temperature zone at 120 °C to 200 °C and in which the rate of atmospheric change is sufficiently rapid for the test.

4.2 Tray, approximately 0,1 m² in area and 25 mm deep, made of non-corrodible material such as stainless steel, tinned steel or aluminium.

4.3 Balance, capable of weighing to the nearest 1 g.

5 Sample

The sample for the determination of total moisture, taken in accordance with ISO 13909-6 shall be kept in a sealed, airtight container. The whole of the sample is crushed to a nominal top size of 16 mm using a jaw crusher. From the crushed material, the laboratory sample is obtained by dividing.

It is essential that precautions be taken to prevent change of moisture during these operations, by undue ventilation, contact with wet surfaces, etc. or loss of sample as dust.

Samples which are visibly wet, and those for which the moisture is expected to exceed 15 %, are partially dried (air-dried) before reduction and division. This air-drying procedure is described in ISO 13909-6 and the resulting air-dry loss is calculated to the nearest 0,1 % (X). The air drying of visibly wet samples shall be carried out in the laboratory in which the determination of the moisture remaining after air-drying (M) is carried out.

6 Procedure

Weigh the clean, dry, empty tray (4.2) to the nearest 1 g (m_1). Add about 1 000 g \pm 100 g of the laboratory sample, spread the coke evenly and reweigh to the nearest 1 g (m_2). Place the charged tray in the

oven (4.1) at a temperature of 120 °C to 200 °C. After the drying period is complete, remove the tray with the dried sample from the oven. Immediately reweigh the tray plus dried sample to the nearest 1 g (m_3) to avoid absorption of moisture during cooling.

If there is any doubt that drying is not complete, reheat at 120 °C to 200 °C for further periods of heating until any change in mass does not exceed 0,1 % mass fraction.

For a particular oven, the times required to ensure constancy in mass shall be verified by experiments.

NOTE If appropriate, the drying can be done at a lower temperature, e.g. 105 °C to 110 °C as for hard coal.

7 Expression of results

7.1 Sample as analysed (see Clause 6)

The total moisture, M_T , of the coke as analysed, expressed as mass fraction in percent, is given by Equation (1):

$$M_T = \frac{m_2 - m_3}{m_2 - m_1} \times 100 \quad (1)$$

where

m_1 is the mass, in grams, of the empty tray;

m_2 is the mass, in grams, of the tray plus coke before heating;

m_3 is the mass, in grams, of the tray plus coke after heating.

Report the result, as the mean of duplicate determinations, to the nearest 0,1 % mass fraction.

7.2 Visibly wet sample (see Clause 5)

For visibly wet samples, the total moisture M_T , expressed as a percentage by mass, is given by Equation (2):

$$M_T = X + M \left(1 - \frac{X}{100} \right) \quad (2)$$

where

X is the air-drying loss, as mass fraction in percent, of the original sample;

M is the residual moisture, as mass fraction in percent, determined on the air-dried laboratory sample.

8 Precision

8.1 Repeatability limit

The results of duplicate determinations (carried out over a short period of time, but not simultaneously) in the same laboratory, by the same operator, with the same apparatus on two representative portions taken from the same analysis sample, shall not differ by more than the value shown in [Table 1](#).