

NFPA[®]

705

**Recommended Practice
for a Field Flame Test
for Textiles and Films**

2018



IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® STANDARDS

NOTICE AND DISCLAIMER OF LIABILITY CONCERNING THE USE OF NFPA STANDARDS

NFPA® codes, standards, recommended practices, and guides (“NFPA Standards”), of which the document contained herein is one, are developed through a consensus standards development process approved by the American National Standards Institute. This process brings together volunteers representing varied viewpoints and interests to achieve consensus on fire and other safety issues. While the NFPA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in NFPA Standards.

The NFPA disclaims liability for any personal injury, property, or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on NFPA Standards. The NFPA also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making NFPA Standards available, the NFPA is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is the NFPA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

The NFPA has no power, nor does it undertake, to police or enforce compliance with the contents of NFPA Standards. Nor does the NFPA list, certify, test, or inspect products, designs, or installations for compliance with this document. Any certification or other statement of compliance with the requirements of this document shall not be attributable to the NFPA and is solely the responsibility of the certifier or maker of the statement.

REVISION SYMBOLS IDENTIFYING CHANGES FROM THE PREVIOUS EDITION

Text revisions are shaded. A **Δ** before a section number indicates that words within that section were deleted and a **Δ** to the left of a table or figure number indicates a revision to an existing table or figure. When a chapter was heavily revised, the entire chapter is marked throughout with the **Δ** symbol. Where one or more sections were deleted, a **•** is placed between the remaining sections. Chapters, annexes, sections, figures, and tables that are new are indicated with an **N**.

Note that these indicators are a guide. Rearrangement of sections may not be captured in the markup, but users can view complete revision details in the First and Second Draft Reports located in the archived revision information section of each code at www.nfpa.org/docinfo. Any subsequent changes from the NFPA Technical Meeting, Tentative Interim Amendments, and Errata are also located there.

REMINDER: UPDATING OF NFPA STANDARDS

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Standards”) should be aware that NFPA Standards may be amended from time to time through the issuance of a Tentative Interim Amendment (TIA) or corrected by Errata. An official NFPA Standard at any point in time consists of the current edition of the document together with any TIAs and Errata then in effect.

To determine whether an NFPA Standard has been amended through the issuance of Tentative Interim Amendments or corrected by Errata, go to www.nfpa.org/docinfo to choose from the list of NFPA Standards or use the search feature to select the NFPA Standard number (e.g., NFPA 13). The document information page provides up-to-date document-specific information as well as postings of all existing TIAs and Errata. It also includes the option to register for an “Alert” feature to receive an automatic email notification when new updates and other information are posted regarding the document.

IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® STANDARDS

ADDITIONAL NOTICES AND DISCLAIMERS

Updating of NFPA Standards

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Standards”) should be aware that these documents may be superseded at any time by the issuance of new editions or may be amended from time to time through the issuance of Tentative Interim Amendments or corrected by Errata. An official NFPA Standard at any point in time consists of the current edition of the document together with any Tentative Interim Amendments and any Errata then in effect. In order to determine whether a given document is the current edition and whether it has been amended through the issuance of Tentative Interim Amendments or corrected through the issuance of Errata, consult appropriate NFPA publications such as the National Fire Codes® Subscription Service, visit the NFPA website at www.nfpa.org, or contact the NFPA at the address listed below.

Interpretations of NFPA Standards

A statement, written or oral, that is not processed in accordance with Section 6 of the Regulations Governing the Development of NFPA Standards shall not be considered the official position of NFPA or any of its Committees and shall not be considered to be, nor be relied upon as, a Formal Interpretation.

Patents

The NFPA does not take any position with respect to the validity of any patent rights referenced in, related to, or asserted in connection with an NFPA Standard. The users of NFPA Standards bear the sole responsibility for determining the validity of any such patent rights, as well as the risk of infringement of such rights, and the NFPA disclaims liability for the infringement of any patent resulting from the use of or reliance on NFPA Standards.

NFPA adheres to the policy of the American National Standards Institute (ANSI) regarding the inclusion of patents in American National Standards (“the ANSI Patent Policy”), and hereby gives the following notice pursuant to that policy:

NOTICE: The user’s attention is called to the possibility that compliance with an NFPA Standard may require use of an invention covered by patent rights. NFPA takes no position as to the validity of any such patent rights or as to whether such patent rights constitute or include essential patent claims under the ANSI Patent Policy. If, in connection with the ANSI Patent Policy, a patent holder has filed a statement of willingness to grant licenses under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, copies of such filed statements can be obtained, on request, from NFPA. For further information, contact the NFPA at the address listed below.

Law and Regulations

Users of NFPA Standards should consult applicable federal, state, and local laws and regulations. NFPA does not, by the publication of its codes, standards, recommended practices, and guides, intend to urge action that is not in compliance with applicable laws, and these documents may not be construed as doing so.

Copyrights

NFPA Standards are copyrighted. They are made available for a wide variety of both public and private uses. These include both use, by reference, in laws and regulations, and use in private self-regulation, standardization, and the promotion of safe practices and methods. By making these documents available for use and adoption by public authorities and private users, the NFPA does not waive any rights in copyright to these documents.

Use of NFPA Standards for regulatory purposes should be accomplished through adoption by reference. The term “adoption by reference” means the citing of title, edition, and publishing information only. Any deletions, additions, and changes desired by the adopting authority should be noted separately in the adopting instrument. In order to assist NFPA in following the uses made of its documents, adopting authorities are requested to notify the NFPA (Attention: Secretary, Standards Council) in writing of such use. For technical assistance and questions concerning adoption of NFPA Standards, contact NFPA at the address below.

For Further Information

All questions or other communications relating to NFPA Standards and all requests for information on NFPA procedures governing its codes and standards development process, including information on the procedures for requesting Formal Interpretations, for proposing Tentative Interim Amendments, and for proposing revisions to NFPA standards during regular revision cycles, should be sent to NFPA headquarters, addressed to the attention of the Secretary, Standards Council, NFPA, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101; email: stds_admin@nfpa.org.

For more information about NFPA, visit the NFPA website at www.nfpa.org. All NFPA codes and standards can be viewed at no cost at www.nfpa.org/docinfo.

Copyright © 2017 National Fire Protection Association®. All Rights Reserved.

NFPA® 705

Recommended Practice for a

Field Flame Test for Textiles and Films

2018 Edition

This edition of NFPA 705, *Recommended Practice for a Field Flame Test for Textiles and Films*, was prepared by the Technical Committee on Fire Tests. It was issued by the Standards Council on November 10, 2017, with an effective date of November 30, 2017, and supersedes all previous editions.

This edition of NFPA 705 was approved as an American National Standard on November 30, 2017.

Origin and Development of NFPA 705

The 1993 edition of NFPA 705 was a complete revision of what was Chapter 10, Field Test: Match Flame Test, in the 1989 edition of NFPA 701, *Standard Methods of Fire Tests for Flame-Resistant Textiles and Films*. Due to the lack of data demonstrating a relationship between the field match test and NFPA 701 small- or large-scale testing, the Committee determined it would be appropriate to create this document so as not to perpetuate any application of a correlation. The field match test does not incorporate the more rigorous laboratory testing methods incorporated into the small- and large-scale testing such as conditioning of specimen, reproducibility, and repeatability. The revisions to NFPA 705 incorporated an increase in safety precautions during the testing procedure, type of ignition source, and removal of sample prior to testing.

The 1997 edition of NFPA 705 was a reconfirmation of the earlier edition.

For the 2003 edition, the chapter layout of NFPA 705 was reorganized to meet the *Manual of Style for NFPA Technical Committee Documents*.

The 2009 edition added references to ASTM E84, *Standard Test Method for Surface Burning Characteristics of Building Materials*, and NFPA 265, *Standard Methods of Fire Tests for Evaluating Room Fire Growth Contribution of Textile or Expanded Vinyl Wall Coverings on Full Height Panels and Walls*, for testing interior finish materials.

The 2013 edition updated referenced standards and terminology. A new section and annex note were added to clarify that NFPA 705 should not be used for textile coverings.

The 2018 edition includes revised scope language to help clarify the use of NFPA 265 for items such as expanded vinyl wall coverings and ceiling coverings.

Technical Committee on Fire Tests

Barry L. Badders, Jr., *Chair*
Intertek Testing Services, TX [RT]

Scott W. Adams, Park City Fire Service District, UT [E]
Farid Alfawakhiri, American Iron and Steel Institute, IL [M]
James A. Burns, New York State Department, NY [E]
Karen C. Carpenter, Southwest Research Institute, TX [RT]
Gordon H. Damant, Inter-City Testing & Consulting Corp. of California, CA [SE]
Rick D. Davis, National Institute of Standards & Technology, MD [RT]
Scott E. Dillon, Crane Engineering, MN [SE]
William E. Fitch, Phyrefish.com, FL [SE]
Richard G. Gann, Gaithersburg, MD [SE]
Marcelo M. Hirschler, GBH International, CA [SE]
Paul A. Hough, Armstrong World Industries, Inc., PA [M]
William E. Koffel, Koffel Associates, Inc., MD [SE]
Sergei V. Levchik, Israel Chemicals Ltd. (ICL-IP), NY [M]
 Rep. ACC-North American Flame Retardant Alliance

James Andrew Lynch, The Fire Solutions Group, PA [SE]
John Martell, Professional Fire Fighters of Maine/IAFF, ME [L]
 Rep. International Association of Fire Fighters
Rodney A. McPhee, Canadian Wood Council, Canada [M]
Kathleen A. Newman, Firetect, CA [M]
Arthur J. Parker, JENSEN HUGHES, MD [SE]
Michael L. Savage, Sr., City of Rio Rancho, NM [E]
Michael Schmeida, Gypsum Association, OH [M]
David T. Sheppard, U.S. Bureau of Alcohol, Tobacco, Firearms & Explosives, MD [RT]
Dwayne E. Sloan, UL LLC, NC [RT]
Stanislav I. Stoliarov, University of Maryland, MD [SE]
Kuma Sumathipala, American Wood Council, VA [M]
Dong Zeng, FM Global, MA [I]
 Rep. FM Global

Alternates

Erik H. Anderson, Koffel Associates, Inc., MD [SE]
 (Alt. to William E. Koffel)

Jesse J. Beitel, JENSEN HUGHES, MD [SE]
 (Alt. to Arthur J. Parker)

Richard J. Davis, FM Global, MA [I]
 (Alt. to Dong Zeng)

Timothy Earl, GBH International, MI [SE]
 (Alt. to Marcelo M. Hirschler)

Sam W. Francis, American Wood Council, PA [M]
 (Alt. to Kuma Sumathipala)

Stephen Paul Fuss, U.S. Bureau of Alcohol, Tobacco, Firearms & Explosives, MD [RT]
 (Alt. to David T. Sheppard)

Justin A. Geiman, Fire and Risk Alliance LLC, MD [SE]
 (Alt. to James Andrew Lynch)

Karl Dana Houser, Intertek, PA [RT]
 (Alt. to Barry L. Badders, Jr.)

Marc L. Janssens, Southwest Research Institute, TX [RT]
 (Alt. to Karen C. Carpenter)

Ineke Van Zeeland, Canadian Wood Council, Canada [M]
 (Alt. to Rodney A. McPhee)

Matthew T. Vinci, International Association of Fire Fighters, DC [L]
 (Alt. to John Martell)

Robert J. Wills, American Iron and Steel Institute, AL [M]
 (Alt. to Farid Alfawakhiri)

Luke C. Woods, UL LLC, MA [RT]
 (Alt. to Dwayne E. Sloan)

Joe Ziolkowski, American Furniture Manufacturers Association, NC [M]
 (Voting Alternate)

Nonvoting

Robert H. Barker, American Fiber Manufacturers Association, VA [M]
 Rep. American Fiber Manufacturers Association

Rohit Khanna, U.S. Consumer Product Safety Commission, MD [C]
 Rep. U.S. Consumer Product Safety Commission

Tracy L. Vecchiarelli, NFPA Staff Liaison

This list represents the membership at the time the Committee was balloted on the final text of this edition. Since that time, changes in the membership may have occurred. A key to classifications is found at the back of the document.

NOTE: Membership on a committee shall not in and of itself constitute an endorsement of the Association or any document developed by the committee on which the member serves.

Committee Scope: This Committee shall have primary responsibility for documents on fire testing procedures, for reviewing existing fire test standards and recommending appropriate action to NFPA, for recommending the application of and advising on the interpretation of acceptable test standards for fire problems of concern to NFPA technical committees and members, and for acting in a liaison capacity between NFPA and the committees of other organizations writing fire test standards. This Committee does not cover fire tests that are used to evaluate extinguishing agents, devices, or systems.

Contents

Chapter 1 Administration	705- 4	Chapter 4 Procedure	705- 5
1.1 Scope.	705- 4	4.1 Materials.	705- 5
1.2 Purpose.	705- 4	4.2 Open Flame.	705- 5
1.3 Application.	705- 4	4.3 Method.	705- 5
Chapter 2 Referenced Publications	705- 5	4.4 Requirements.	705- 6
2.1 General.	705- 5	Chapter 5 Summary	705- 6
2.2 NFPA Publications.	705- 5	5.1 Limitations.	705- 6
2.3 Other Publications.	705- 5	5.2 Precautions.	705- 6
2.4 References for Extracts in Recommendations Sections. (Reserved)	705- 5	Annex A Explanatory Material	705- 6
Chapter 3 Definitions	705- 5	Annex B Informational References	705- 7
3.1 General.	705- 5	Index	705- 8
3.2 NFPA Official Definitions.	705- 5		
3.3 General Definitions.	705- 5		

NFPA 705

Recommended Practice for a

Field Flame Test for Textiles and Films

2018 Edition

IMPORTANT NOTE: This NFPA document is made available for use subject to important notices and legal disclaimers. These notices and disclaimers appear in all publications containing this document and may be found under the heading "Important Notices and Disclaimers Concerning NFPA Standards." They can also be viewed at www.nfpa.org/disclaimers or obtained on request from NFPA.

UPDATES, ALERTS, AND FUTURE EDITIONS: New editions of NFPA codes, standards, recommended practices, and guides (i.e., NFPA Standards) are released on scheduled revision cycles. This edition may be superseded by a later one, or it may be amended outside of its scheduled revision cycle through the issuance of Tentative Interim Amendments (TIAs). An official NFPA Standard at any point in time consists of the current edition of the document, together with all TIAs and Errata in effect. To verify that this document is the current edition or to determine if it has been amended by TIAs or Errata, please consult the National Fire Codes® Subscription Service or the "List of NFPA Codes & Standards" at www.nfpa.org/docinfo. In addition to TIAs and Errata, the document information pages also include the option to sign up for alerts for individual documents and to be involved in the development of the next edition.

NOTICE: An asterisk (*) following the number or letter designating a paragraph indicates that explanatory material on the paragraph can be found in Annex A.

A reference in brackets [] following a section or paragraph indicates material that has been extracted from another NFPA document. As an aid to the user, the complete title and edition of the source documents for extracts in mandatory sections of the document are given in Chapter 2 and those for extracts in informational sections are given in Annex B. Extracted text may be edited for consistency and style and may include the revision of internal paragraph references and other references as appropriate. Requests for interpretations or revisions of extracted text shall be sent to the technical committee responsible for the source document.

Information on referenced publications can be found in Chapter 2 and Annex B.

Chapter 1 Administration

1.1 Scope.

1.1.1 This recommended practice provides guidance to enforcement officials for the field application of an open flame to textiles and films that have been in use in the field or for which reliable laboratory data are not available.

▲ 1.1.2 There is no known correlation between this recommended practice and NFPA 701 or full-scale fire behavior.

1.2 Purpose.

1.2.1 The purpose of this recommended practice is to provide authorities having jurisdiction with a field means of determining the tendency of textiles and films to sustain burning subsequent to the application of a relatively small open flame.

1.2.2 The methods described herein and the results do not correlate with any known test method, and factors relating to reproducibility and correlation have not been determined; therefore, they should not be relied upon when more definitive test data are available.

1.3 Application.

1.3.1 These recommendations apply to materials used in the interior of buildings, for protective outdoor coverings such as tarpaulins and tents, and for plastic films (with or without reinforcing or backing) used for decorative or other purposes inside buildings or as temporary or permanent enclosures for buildings under construction.

1.3.1.1* The field test method can be useful to regulatory officials as an indicator of whether a material being used or **installed** burns very easily or can be flame resistant as indicated by the following:

- (1) Cessation of burning when the igniting flame is removed
- (2) Failure to burn at all
- (3) Continuing to burn nonaggressively after the igniting flame is removed

1.3.1.2 The field test method has utility only when the authority having jurisdiction has no reliable data and, therefore, is forced to rely solely on the field test findings.

1.3.1.3 There are only two types of materials for which the field test method can be deemed to provide foolproof and totally adequate results: those made entirely of noncombustible inorganic material and those that ignite and burn readily on exposure to a small flame. For example, with only limited experience, an inspector will have no difficulty in identifying an all-mineral fiber fabric by employing a small open flame, and no other procedure is necessary. The only effect a small fire exposure has on a mineral fiber fabric is to burn off the surface coloring, if any, leaving the threads themselves virtually undamaged. This result is not obtained with any other type of decorative fabric and, therefore, is readily recognized. At the other extreme, if a material ignites and burns readily from the application of a small open flame from a source such as a kitchen match, showing no semblance of flame resistance, no other procedure is necessary, since the material obviously is not acceptable.

1.3.1.4 Between these two extremes, the field test method has a limited and varying degree of reliability. Within this large group, which comprises the great majority of materials the enforcement official is likely to encounter in the field, the most reliable results are obtained in the testing of cellulose-based materials (cotton, rayon, and paper) that are flame retardant-treated with the common inorganic salt formulations. These materials retain their shape reasonably during testing, and the results are not greatly affected by differences in sample size or severity of fire exposure. However, the least-reliable results are obtained with chemically treated fabrics of synthetic fibers or flexible plastic films and laminates. These materials are subject to a variety of physical changes when exposed to fire, such as shrinking, curling, melting, elongating, and similar distortions, making the examination of small samples quite difficult and the results ambiguous. Furthermore, some of these thermoplastic materials are apt to appear flame resistant with small flame exposures but ignite and burn fiercely with longer exposures to larger ignition sources.

1.3.2* This recommended practice should not be used to determine that a textile material or a film is flame retardant.

1.3.3* This recommended practice does not apply to textile wall coverings or to textile ceiling coverings.

Δ 1.3.4 Materials applied to surfaces of buildings or backing materials as interior finishes in buildings should be tested and classified in accordance with NFPA 286 or ASTM E84, *Standard Test Method for Surface Burning Characteristics of Building Materials*, with the provisions required by presiding codes or regulations.

N 1.3.4.1 In the case of textile wall coverings and expanded vinyl wall coverings, the use of NFPA 265 is also appropriate, with some limitations.

N 1.3.4.2 Ceiling coverings should not be tested using NFPA 265, because the test flame does not reach the ceiling.

Chapter 2 Referenced Publications

2.1 General. The documents or portions thereof listed in this chapter are referenced within this recommended practice and should be considered part of the recommendations of this document.

2.2 NFPA Publications. National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 265, *Standard Methods of Fire Tests for Evaluating Room Fire Growth Contribution of Textile or Expanded Vinyl Wall Coverings on Full Height Panels and Walls*, 2015 edition.

NFPA 286, *Standard Methods of Fire Tests for Evaluating Contribution of Wall and Ceiling Interior Finish to Room Fire Growth*, 2015 edition.

NFPA 701, *Standard Methods of Fire Tests for Flame Propagation of Textiles and Films*, 2015 edition.

2.3 Other Publications.

2.3.1 ASTM Publications. ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959.

ASTM E84, *Standard Test Method for Surface Burning Characteristics of Building Materials*, 2016.

2.3.2 Other Publications.

Merriam-Webster's Collegiate Dictionary, 11th edition, Merriam-Webster, Inc., Springfield, MA, 2003.

2.4 References for Extracts in Recommendations Sections. (Reserved)

Chapter 3 Definitions

3.1 General. The definitions contained in this chapter apply to the terms used in this recommended practice. Where terms are not defined in this chapter or within another chapter, they should be defined using their ordinarily accepted meanings within the context in which they are used. *Merriam-Webster's Collegiate Dictionary*, 11th edition, is the source for the ordinarily accepted meaning.

3.2 NFPA Official Definitions.

3.2.1* Authority Having Jurisdiction (AHJ). An organization, office, or individual responsible for enforcing the requirements

of a code or standard, or for approving equipment, materials, an installation, or a procedure.

3.2.2 Recommended Practice. A document that is similar in content and structure to a code or standard but that contains only nonmandatory provisions using the word “should” to indicate recommendations in the body of the text.

3.2.3 Should. Indicates a recommendation or that which is advised but not required.

3.2.4 Standard. An NFPA Standard, the main text of which contains only mandatory provisions using the word “shall” to indicate requirements and which is in a form generally suitable for mandatory reference by another standard or code or for adoption into law. Nonmandatory provisions are not to be considered a part of the requirements of a standard and shall be located in an appendix, annex, footnote, informational note, or other means as permitted in the NFPA Manuals of Style. When used in a generic sense, such as in the phrase “standards development process” or “standards development activities,” the term “standards” includes all NFPA Standards, including Codes, Standards, Recommended Practices, and Guides.

3.3 General Definitions.

3.3.1 Film. A flat section of a thermoplastic resin, a regenerated cellulose derivative, or other material that is extremely thin in comparison to its length and breadth and has a nominal maximum thickness of 0.25 mm (0.01 in.).

3.3.2 Kitchen Match. A piece of wood with a combustible mixture at its tip that bursts into flame through friction, with an approximate length of 61.9 mm (2⁷/₁₆ in.) and an approximate weight of 29 g (1 oz) per hundred.

3.3.3 Textile. A material made of natural or man-made fibers and used for the manufacture of items such as curtains, clothing, and furniture fittings.

Chapter 4 Procedure

4.1* Materials.

4.1.1 Specimens should be samples removed from the existing material.

4.1.2 Specimens should be dry and should be a minimum of 12.7 mm × 101.6 mm (½ in. × 4 in.).

4.2 Open Flame. The fire exposure should be from a common wood kitchen match or source with equivalent flame properties.

4.2.1 The flame should be applied for 12 seconds.

4.3* Method.

4.3.1 The test should be performed in a draft-free and safe location free of other combustibles.

4.3.2 The sample should be suspended (preferably by means of a spring clip, tongs, or similar device) with the long axis vertical, the flame supplied to the center of the bottom edge, and the bottom edge 12.7 mm (½ in.) above the bottom of the flame.

4.3.3 After 12 seconds of exposure, the match is to be removed gently away from the sample.

4.4 Requirements. During the exposure, flaming should not spread over the complete length of the sample or, in the case of larger samples, in excess of 101.6 mm (4 in.) from the bottom of the sample.

4.4.1 There should be not more than 2 seconds of afterflame.

4.4.2 Materials that break or drip flaming particles should be rejected if the materials continue to burn after they reach the floor.

Chapter 5 Summary

5.1 Limitations. The deficiencies and limitations of the field test method can lead to misleading or erroneous results, and the error can be in both directions. It is quite possible to have a too-small sample show several seconds of afterflaming, causing the material to be rejected. It is equally possible for improper or inadequate field procedures to incorrectly indicate satisfactory flame resistance. This can result in dangerous errors.

5.2 Precautions. Field procedures are useful, but they must be used with good judgment and their limitations should be recognized. Field tests should not be relied on as the sole means for ensuring adequate flame resistance of decorative materials. They are, however, useful in augmenting a comprehensive regulatory program.

Annex A Explanatory Material

Annex A is not a part of the recommendations of this NFPA document but is included for informational purposes only. This annex contains explanatory material, numbered to correspond with the applicable text paragraphs.

A.1.3.1.1 By far, the greatest benefit can be derived from the field test method when the inspector has had the opportunity to practice and experiment on a variety of decorative materials and particularly to make comparisons between the results of laboratory tests performed in accordance with NFPA 701 and the less-precise field test method. Experience is the best teacher, and it is strongly recommended that inspectors who may be involved in this activity familiarize themselves with a wide variety of treated and inherently flame-resistant fabrics and the typical behavior of those fabrics under a variety of test conditions. With this background, the inspector possesses a greater capability for properly interpreting field test results.

△ A.1.3.2 For many years, codes have used the statement that “materials shall be flame retardant.” When that statement applies to textiles or films, it is intended to mean that the textile or film meets the flame propagation performance criteria contained in NFPA 701.

△ A.1.3.3 The fire performance of textile wall coverings and that of ceiling wall coverings is affected to a significant extent by the types of backing (or substrate) and adhesive used. The most appropriate fire tests for textile and ceiling wall coverings are room-corner tests, including NFPA 286.

A.3.2.1 Authority Having Jurisdiction (AHJ). The phrase “authority having jurisdiction,” or its acronym AHJ, is used in NFPA documents in a broad manner, since jurisdictions and approval agencies vary, as do their responsibilities. Where

public safety is primary, the authority having jurisdiction may be a federal, state, local, or other regional department or individual such as a fire chief; fire marshal; chief of a fire prevention bureau, labor department, or health department; building official; electrical inspector; or others having statutory authority. For insurance purposes, an insurance inspection department, rating bureau, or other insurance company representative may be the authority having jurisdiction. In many circumstances, the property owner or his or her designated agent assumes the role of the authority having jurisdiction; at government installations, the commanding officer or departmental official may be the authority having jurisdiction.

A.4.1 A difficult and controversial question concerns the minimum number of specimens that should be tested. The answer can be dictated by a number of factors. A good general rule is the more specimens, the better; but, in all cases, the inspector should exercise good judgment. The variety of circumstances that can be encountered can be illustrated by some specific examples:

- (1) A dance in a school gymnasium, decorated by students with a profusion of paper banners, crepe paper streamers, figures made of pieces of tissue paper stuffed in chicken-wire molds, hay and straw, painted fabrics, dry palm fronds, and similar products, all alleged to be flame resistant: In this situation, the inspector has neither reason nor excuse to be inhibited in taking samples for tests. The materials are inexpensive and are unlikely to be reused. Taking samples for tests will cause little if any change to the decorative effect.
- (2) A large assembly tent made of supposedly treated canvas but with no identifying marks and no confirming evidence of such treatment: The life hazard is acute, tent canvas can readily be patched, and, therefore, the situation warrants nothing less than sufficient samples from all sections of canvas for the inspector to be satisfied that the quality and uniformity of the treatment are acceptable.
- (3) A nightclub with very expensive draperies known to be adequately flame retardant—treated when installed two years previously: The only way to be certain that the quality of flame resistance remains acceptable is to take a sample, but in the interest of maintaining good public relations, the inspector should be diplomatic and persuasive. Usually, a place can be found where a small but adequate sample can be extracted without causing any visible damage. Often this is the most the inspector can expect to get.

A.4.3 There can be complications of a technical nature. Decorative fabrics sometimes are installed overhead, in or near a horizontal position. Some plastic films or fabrics woven of thermoplastic synthetic fibers will successfully resist continued burning in the normal vertical position of test, but will exhibit continued burning if exposed in a horizontal position. Fabrics or films installed horizontally may be a serious threat to safety in a fire situation, and, therefore, the inspector is justified in testing the material in a horizontal position.

A somewhat similar problem can exist with some of the new and increasingly popular decorative fabrics with one or more types of fibers in the threads along the length (warp) and different fibers in the threads along the width (fill). This can result in a different burning behavior in the two directions of the fabric. In some fabrics where a flame-retardant treatment has been applied, tests for flame resistance in one direction

may be acceptable, but the fabric could show continued burning in the other direction. Where visual examination of the fabric indicates this condition might exist, the inspector should test samples cut with the long dimension paralleling both the length and width of the fabric.

Annex B Informational References

B.1 Referenced Publications. The documents or portions thereof listed in this annex are referenced within the informational sections of this recommended practice and are not part of the recommendations of this document unless also listed in Chapter 2 for other reasons.

B.1.1 NFPA Publications. National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 286, *Standard Methods of Fire Tests for Evaluating Contribution of Wall and Ceiling Interior Finish to Room Fire Growth*, 2015 edition.

NFPA 701, *Standard Methods of Fire Tests for Flame Propagation of Textiles and Films*, 2015 edition.

B.1.2 Other Publications. (Reserved)

B.2 Informational References. (Reserved)

B.3 References for Extracts in Informational Sections. (Reserved)

Index

Copyright © 2017 National Fire Protection Association. All Rights Reserved.

The copyright in this index is separate and distinct from the copyright in the document that it indexes. The licensing provisions set forth for the document are not applicable to this index. This index may not be reproduced in whole or in part by any means without the express written permission of NFPA.

-A- Administration, Chap. 1 Application, 1.3 Purpose, 1.2 Scope, 1.1 Authority Having Jurisdiction (AHJ) Definition, 3.2.1, A.3.2.1	-P- Procedure, Chap. 4 Materials, 4.1, A.4.1 Method, 4.3, A.4.3 Open Flame, 4.2 Requirements, 4.4
-D- Definitions, Chap. 3	-R- Recommended Practice Definition, 3.2.2 Referenced Publications, Chap. 2
-E- Explanatory Material, Annex A	-S- Should
-F- Film Definition, 3.3.1	Definition, 3.2.3 Standard Definition, 3.2.4 Summary, Chap. 5 Limitations, 5.1 Precautions, 5.2
-I- Informational References, Annex B	-T- Textile Definition, 3.3.3
-K- Kitchen Match Definition, 3.3.2	

Sequence of Events for the Standards Development Process

Once the current edition is published, a Standard is opened for Public Input.

Step 1 – Input Stage

- Input accepted from the public or other committees for consideration to develop the First Draft
- Technical Committee holds First Draft Meeting to revise Standard (23 weeks); Technical Committee(s) with Correlating Committee (10 weeks)
- Technical Committee ballots on First Draft (12 weeks); Technical Committee(s) with Correlating Committee (11 weeks)
- Correlating Committee First Draft Meeting (9 weeks)
- Correlating Committee ballots on First Draft (5 weeks)
- First Draft Report posted on the document information page

Step 2 – Comment Stage

- Public Comments accepted on First Draft (10 weeks) following posting of First Draft Report
- If Standard does not receive Public Comments and the Technical Committee chooses not to hold a Second Draft meeting, the Standard becomes a Consent Standard and is sent directly to the Standards Council for issuance (see Step 4) or
- Technical Committee holds Second Draft Meeting (21 weeks); Technical Committee(s) with Correlating Committee (7 weeks)
- Technical Committee ballots on Second Draft (11 weeks); Technical Committee(s) with Correlating Committee (10 weeks)
- Correlating Committee Second Draft Meeting (9 weeks)
- Correlating Committee ballots on Second Draft (8 weeks)
- Second Draft Report posted on the document information page

Step 3 – NFPA Technical Meeting

- Notice of Intent to Make a Motion (NITMAM) accepted (5 weeks) following the posting of Second Draft Report
- NITMAMs are reviewed and valid motions are certified by the Motions Committee for presentation at the NFPA Technical Meeting
- NFPA membership meets each June at the NFPA Technical Meeting to act on Standards with “Certified Amending Motions” (certified NITMAMs)
- Committee(s) vote on any successful amendments to the Technical Committee Reports made by the NFPA membership at the NFPA Technical Meeting

Step 4 – Council Appeals and Issuance of Standard

- Notification of intent to file an appeal to the Standards Council on Technical Meeting action must be filed within 20 days of the NFPA Technical Meeting
- Standards Council decides, based on all evidence, whether to issue the standard or to take other action

Notes:

1. Time periods are approximate; refer to published schedules for actual dates.
2. Annual revision cycle documents with certified amending motions take approximately 101 weeks to complete.
3. Fall revision cycle documents receiving certified amending motions take approximately 141 weeks to complete.

Committee Membership Classifications^{1,2,3,4}

The following classifications apply to Committee members and represent their principal interest in the activity of the Committee.

1. M *Manufacturer*: A representative of a maker or marketer of a product, assembly, or system, or portion thereof, that is affected by the standard.
2. U *User*: A representative of an entity that is subject to the provisions of the standard or that voluntarily uses the standard.
3. IM *Installer/Maintainer*: A representative of an entity that is in the business of installing or maintaining a product, assembly, or system affected by the standard.
4. L *Labor*: A labor representative or employee concerned with safety in the workplace.
5. RT *Applied Research/Testing Laboratory*: A representative of an independent testing laboratory or independent applied research organization that promulgates and/or enforces standards.
6. E *Enforcing Authority*: A representative of an agency or an organization that promulgates and/or enforces standards.
7. I *Insurance*: A representative of an insurance company, broker, agent, bureau, or inspection agency.
8. C *Consumer*: A person who is or represents the ultimate purchaser of a product, system, or service affected by the standard, but who is not included in (2).
9. SE *Special Expert*: A person not representing (1) through (8) and who has special expertise in the scope of the standard or portion thereof.

NOTE 1: “Standard” connotes code, standard, recommended practice, or guide.

NOTE 2: A representative includes an employee.

NOTE 3: While these classifications will be used by the Standards Council to achieve a balance for Technical Committees, the Standards Council may determine that new classifications of member or unique interests need representation in order to foster the best possible Committee deliberations on any project. In this connection, the Standards Council may make such appointments as it deems appropriate in the public interest, such as the classification of “Utilities” in the National Electrical Code Committee.

NOTE 4: Representatives of subsidiaries of any group are generally considered to have the same classification as the parent organization.

Submitting Public Input / Public Comment Through the Online Submission System

Soon after the current edition is published, a Standard is open for Public Input.

Before accessing the Online Submission System, you must first sign in at www.nfpa.org. *Note: You will be asked to sign-in or create a free online account with NFPA before using this system:*

- a. Click on Sign In at the upper right side of the page.
- b. Under the Codes and Standards heading, click on the “List of NFPA Codes & Standards,” and then select your document from the list or use one of the search features.

OR

- a. Go directly to your specific document information page by typing the convenient shortcut link of www.nfpa.org/document# (Example: NFPA 921 would be www.nfpa.org/921). Sign in at the upper right side of the page.

To begin your Public Input, select the link “The next edition of this standard is now open for Public Input” located on the About tab, Current & Prior Editions tab, and the Next Edition tab. Alternatively, the Next Edition tab includes a link to Submit Public Input online.

At this point, the NFPA Standards Development Site will open showing details for the document you have selected. This “Document Home” page site includes an explanatory introduction, information on the current document phase and closing date, a left-hand navigation panel that includes useful links, a document Table of Contents, and icons at the top you can click for Help when using the site. The Help icons and navigation panel will be visible except when you are actually in the process of creating a Public Input.

Once the First Draft Report becomes available there is a Public Comment period during which anyone may submit a Public Comment on the First Draft. Any objections or further related changes to the content of the First Draft must be submitted at the Comment stage.

To submit a Public Comment you may access the online submission system utilizing the same steps as previously explained for the submission of Public Input.

For further information on submitting public input and public comments, go to: <http://www.nfpa.org/publicinput>.

Other Resources Available on the Document Information Pages

About tab: View general document and subject-related information.

Current & Prior Editions tab: Research current and previous edition information on a Standard.

Next Edition tab: Follow the committee’s progress in the processing of a Standard in its next revision cycle.

Technical Committee tab: View current committee member rosters or apply to a committee.

Technical Questions tab: For members and Public Sector Officials/AHJs to submit questions about codes and standards to NFPA staff. Our Technical Questions Service provides a convenient way to receive timely and consistent technical assistance when you need to know more about NFPA codes and standards relevant to your work. Responses are provided by NFPA staff on an informal basis.

Products & Training tab: List of NFPA’s publications and training available for purchase.