

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 4006 A

Issued 11-1-41

Revised 4-1-46

### ALUMINUM ALLOY SHEET Manganese (3S-0)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **COMPOSITION:**

Manganese	1.0 - 1.5
Iron	0.70 max
Silicon	0.60 max
Copper	0.20 max
Zinc	0.10 max
Other Elements, each	0.05 max
Other Elements, total	0.15 max
Aluminum	remainder

3. **CONDITION:** (a) Annealed and unless otherwise specified, mill finish.

(b) Physical properties shall conform to the values in the following table. Test specimens shall conform to ASTM E-8, except from sheet less than 3/4 inch in width. Elongation requirements apply only to sheet 3/4 inch and over in width.

<u>Thickness</u> Inch	<u>Tensile Strength</u> psi max	<u>Elongation</u> % in 2 in. min
0.006 - 0.007, incl.	19,000	14
0.008 - 0.012, incl.	19,000	18
0.013 - 0.031, incl.	19,000	20
0.032 - 0.050, incl.	19,000	23
0.051 - 0.249, incl.	19,000	25

(c) Sheet shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to direction of rolling.

4. **QUALITY:** (a) Sheet shall be uniform in quality and condition, clean, sound, and free from foreign material and from internal and external defects detrimental to fabrication or to the appearance and performance of parts. Sheet revealing defects during fabrication shall be subject to rejection.

(b) Sheet and parts made therefrom shall be subjected to inspection by any method which will reveal defects.

5. **TOLERANCES:** Unless otherwise specified, tolerances shall conform to the latest revision of AMS 2202 as applicable. Thickness tolerances shall conform to Table I.

6. **REPORTS:** (a) Unless otherwise specified, the vendor of sheet shall furnish three copies of a notarized report stating that the sheet meets all the requirements of this specification. This report shall include the purchase order number, material specification number, size and quantity.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to the standard or recommended practice, and no commitment to the standard or recommended practice, and its Committee will not investigate or consider any action which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."