



SAE The Engineering
Resource For
Advancing Mobility

400 COMMONWEALTH DRIVE WARRENDALE PA 15096

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 5728B

Issued 12-1-51
Revised 10-1-82

**STEEL FORGINGS, CORROSION AND HEAT RESISTANT
16Cr - 25Ni - 6Mo
Hopkins Electric Ingot Process**

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 10-29-68. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "B" revision of the subject specification.

.....

This specification has been declared "~~CANCELLED~~" by the Aerospace Materials Division, SAE, as of 10-1-82. By this action, subject specification number and title will be deleted from the active specification index of Aerospace Material Specifications.

This specification is under the jurisdiction of AMS Committee "F".

SAE Technical Board rules provide that "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.2.3 The forging shall be hot-cold worked as follows: It shall, in a period of 4 - 6 hr, be heated uniformly throughout to a temperature of 1225 - 1260 F and then worked to finished size in suitable dies either by pressing or hammering.
- 5.2.4 Forgings shall be stress relieved by heating to 1200 - 1220 F, holding at heat for not less than 10 hr, and cooling in still air, unless otherwise agreed upon by purchaser and vendor.

6. TECHNICAL REQUIREMENTS:

- 6.1 Tensile Properties: Unless otherwise specified, specimens cut from forgings with the axis approximately parallel to the forging flow lines shall conform to the following requirements:

Tensile Strength, psi	100,000 min
Yield Strength at 0.2% Offset or at 0.0096 in. in 2 in. Extension Under Load (E = 20,500,000), psi	60,000 min
Elongation, % in 4D	10 min
Reduction of Area, %	15 min

- 6.2 Hardness: Unless otherwise specified, forgings shall have hardness of Brinell 235 - 293 or equivalent.

- 6.3 Stress-Rupture Test at 1200 F: Specimens cut from forgings with the axis approximately parallel to the forging flow lines shall be capable of meeting the following requirements:

- 6.3.1 A tensile test specimen, maintained at 1200 F \pm 3 while an axial stress of 40,000 psi is applied continuously, shall not rupture in less than 100 hours. The test shall be continued, after the 100 hr, until the specimen ruptures, either maintaining the same stress or increasing the stress to not over 45,000 psi as necessary to produce rupture. In either case, the elongation after rupture, measured at room temperature, shall be not less than 5% in 4D.

7. QUALITY:

- 7.1 Material shall be multiple melted using the Hopkins electric arc melting process with flux cover in the final melting and shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
- 7.2 Inspection standards and procedures shall be as agreed upon by purchaser and vendor.

8. REPORTS:

- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each ingot lot in the shipment and the results of tests on each ingot lot to determine conformance to the technical requirements of this specification.
- This report shall include the purchase order number, part number or size, ingot lot number, serial number of each forging when required, ingot number, and position of forging stock in ingot when such information is available, material specification number, and quantity from each ingot lot. Ingot lot number is a number applied to a multiple melted ingot or a group of multiple melted ingots made from one master melt of material.