

AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 5744

Issued 2-15-65
Revised

STEEL BARS AND FORGINGS, CORROSION AND MODERATE HEAT RESISTANT

15.5Cr - 4.5Ni - 2.9Mo - 0.10N
Heat Treated (170,000 psi Tensile)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars, forgings, and forging stock.
3. **APPLICATION:** Primarily for parts and assemblies requiring high strength and oxidation resistance up to 800 F (427 C), improved mechanical properties and resistance to stress corrosion, where parts can be machined from fully heat treated material to eliminate the need for heat treatment by the user.
4. **COMPOSITION:**

	min	max
Carbon	0.10	0.15
Manganese	0.50	1.25
Silicon	--	0.50
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	15.00	16.00
Nickel	4.00	5.00
Molybdenum	2.50	3.25
Nitrogen	0.07	0.13

- 4.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2248.
5. **CONDITION:**
 - 5.1 **Bars and Forgings:** Solution heat treated, sub-zero cooled, austenite conditioned, sub-zero cooled, tempered, and descaled.
 - 5.2 **Forging Stock:** As ordered by the forging manufacturer.
6. **TECHNICAL REQUIREMENTS:**
 - 6.1 **Heat Treatment:** The product shall be solution treated by heating to $1900\text{ F} \pm 25$ ($1037.8\text{ C} \pm 14$), holding at heat for 1 - 3 hr, and quenching in water; cooled to not higher than -100 F (-73 C), held at this temperature for not less than 3 hr, and warmed in air to room temperature; austenite conditioned by heating to $1750\text{ F} \pm 25$ ($954.4\text{ C} \pm 14$), holding at heat for not less than 10 min. but not more than 1 hr, and quenching in water or otherwise cooling as rapidly as possible to room temperature; cooled to not higher than -100 F (-73 C), held at this temperature for not less than 3 hr, and warmed in air to room temperature; and tempered by heating to $1000\text{ F} \pm 25$ ($537.8\text{ C} \pm 14$), holding at heat for not less than 3 hr, and cooling in air.

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and applying technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."