

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 6535 A

Issued 9-1-42

Revised 10-1-43

STEEL TUBING (SEAMLESS) ROUND
.55 Ni .5 Cr .25 Mo (.33-.38 C)
(Normalized)

1. ACKNOWLEDGMENT: A vendor must mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

| | Individual Tube Check Analysis | Over or Under |
|------------|-----------------------------------|---------------|
| Carbon | 0.33 - 0.38 | 0.02 |
| Manganese | 0.75 - 1.00 | 0.04 |
| Phosphorus | 0.040 max | 0.005 |
| Sulphur | 0.040 max | 0.005 |
| Silicon | 0.20 - 0.35 | 0.02 |
| Nickel | 0.40 - 0.70 | 0.03 |
| Chromium | 0.40 - 0.60 | 0.03 |
| Molybdenum | 0.20 - 0.30 | 0.03 |

3. GRAIN SIZE: 5 or finer as determined on the billet, ASTM E19-39T, method a, unless otherwise ordered. A heat of steel predominately 5 or finer with grains as large as 3 is permissible.

4. CONDITION: Normalized, then stress relieved if cold worked after the normalizing, to conform to the following minimum physical properties, unless otherwise ordered:

| Nominal Wall Thickness Inch | Tensile Strength lb per sq in. | Yield Strength at 0.2% Set or at Extension Indicated | | Elongation in 2" Extension Under Load | | Full Tube Strip % | |
|--------------------------------|--------------------------------------|---|------------|---|----|----------------------|---|
| | | lb per sq in. | inch in 2" | inch in 2" | % | % | % |
| Up to 0.188, incl. | 100,000 | 85,000 | 0.0097 | 12 | 7 | | |
| Over 0.188 | 95,000 | 80,000 | 0.0093 | 15 | 10 | | |

5. QUALITY: (a) This material must be aircraft quality, uniform in temper and must not reveal injurious defects during the fabrication processes.

(b) Finished parts may be subject to magnetic inspection.

(c) The tubing shall have a good workmanlike finish conforming to the best practice for high quality aircraft material. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious defects. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered as injurious defects, provided the imperfections are removable within the tolerances specified herein for diameter and wall thickness. The removal of surface imperfections is not required.