



SURFACE VEHICLE STANDARD

J409™**JUL2021**

Issued 1942-01
Reaffirmed 1995-02
Revised 2021-07

Superseding J409 FEB1995

Product Analysis - Permissible Variations from Specified Chemical Analysis of a Heat or Cast of Steel

RATIONALE

Table values needed updating to align with referenced ASTM standards.

1. SCOPE

Supplementary to the heat or cast analysis, a product analysis may be made on steel in the semifinished or finished form. For definitions and methods of sampling steel for product chemical analysis, refer to SAE J408.

A product analysis is a chemical analysis of the semifinished or finished steel to determine conformance to the specification requirements. The range of the specified chemical composition is normally expanded to take into account deviations associated with analytical reproducibility and the heterogeneity of the steel. Individual determinations may vary from the specified heat or cast analysis ranges or limits to the extent shown in Tables 1 through 5. The several determinations of any element in a heat or cast may not vary both above and below the specified range except for lead. Tables 1 through 5 provide permissible limits for various steel forms and composition types.

For rephosphorized and resulfurized steels, the product analysis tolerance limits are not applicable to phosphorus and sulfur because of the degree to which these elements segregate.

Boron is not subject to product analysis tolerances.

2. REFERENCES

2.1 Applicable Documents

The following publications form a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.1.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

SAE J408 Methods of Sampling Steel for Chemical Analysis

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
https://www.sae.org/standards/content/J409_202107

2.1.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A6/A6M	Specification for General Requirements for Rolled Steel Plates, Shapes, Sheet Piling, and Bars for Structural Use
ASTM A480/A480M	Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM A513/A513M	Specification for Electric-Resistance-Welded Carbon and Alloy Steel Mechanical Tubing
ASTM A519/A519M	Specification for Seamless Carbon and Alloy Steel Mechanical Tubing

Table 1 - Permissible variations from specified chemical ranges and limits for carbon steel in hot rolled and cold finished bars and semi-finished products for forging, wire rod, and seamless tubing

Element	Limit or Max of Specified Range, %	Variation, %, Over Max Limit or Under Min Limit Bars, Wire Rod, Seamless Tubing and Semifinished Products for Forging to 0.065 m ² (100 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products for Forging Over 0.065 to 0.129 m ² (100 to 200 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products for Forging Over 0.129 to 0.258 m ² (200 to 400 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products for Forging Over 0.258 to 0.516 m ² (400 to 800 in ²) incl
Carbon	To 0.25 incl	0.02	0.03	0.04	0.05
	Over 0.25 to 0.55 incl	0.03	0.04	0.05	0.06
	Over 0.55	0.04	0.05	0.06	0.07
Manganese	To 0.90 incl	0.03	0.04	0.06	0.07
	Over 0.90 to 1.65 incl	0.06	0.06	0.07	0.08
Phosphorus	Over max only to 0.050 incl	0.008	0.008	0.010	0.015
Sulfur	Over max only to 0.060 incl	0.008	0.010	0.010	0.015
Silicon	To 0.35 incl	0.02	0.02	0.03	0.04
	Over 0.35 to 0.60	0.05	—	—	—
Copper	Under min only for copper bearing steels	0.02	0.03	—	—
Lead ¹	0.15 to 0.35 incl	0.03	0.03	—	—

¹ Product analysis tolerance for lead applies, both over and under, to a range of 0.15 to 0.35% lead.

Table 2 - Permissible variations from specified chemical ranges and limits for carbon steel sheets, strip, and welded tubing

Element	Limit or Max of Specified Range, %	Limit Variation, % Under Min Limit	Limit Variation, % Over Max Limit
Carbon	To 0.15 incl	0.02	0.03
	Over 0.15 to 0.40 incl	0.03	0.04
	Over 0.40 to 0.80 incl	0.03	0.05
	Over 0.80	0.03	0.06
Manganese	To 0.60 incl	0.03	0.03
	Over 0.60 to 1.15 incl	0.04	0.04
	Over 1.15 to 1.65 incl	0.05	0.05
Phosphorus	—	—	0.010
Sulfur	—	—	0.010
Silicon	To 0.30 incl	0.02	0.03
	Over 0.30 to 0.60	0.05	0.05
Copper	Under min only for copper bearing steels	0.02	—
Lead ¹	0.15 to 0.35 incl	0.03	0.03

¹ Product analysis tolerance for lead applies, both over and under, to a range of 0.15 to 0.35% lead.

Table 3 - Permissible variations from specified chemical ranges and limits for alloy steels

Element	Limit or Max of Specified Range, %	Variation, %, Over Max Limit or Under Min Limit Bars, Sheet, Strip, Tubing, and Semifinished Products to 0.0645 m ² (100 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products Over 0.0645 to 0.129 m ² (100 to 200 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products Over 0.129 to 0.258 m ² (200 to 400 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products Over 0.258 to 0.516 m ² (400 to 800 in ²) incl
Carbon	To 0.30 incl	0.01	0.02	0.03	0.04
	Over 0.30 to 0.75 incl	0.02	0.03	0.04	0.05
	Over 0.75	0.03	0.04	0.05	0.06
Manganese	To 0.90 incl	0.03	0.04	0.05	0.06
	Over 0.90 to 2.10 incl	0.04	0.05	0.06	0.07
Phosphorus	Over max only	0.005	0.010	0.010	0.010
Sulfur	To 0.060 incl	0.005	0.010	0.010	0.010
Silicon	To 0.35 incl	0.02	0.02	0.03	0.04
	Over 0.35 to 2.20 incl	0.05	0.06	0.06	0.07
Nickel	To 1.00 incl	0.03	0.03	0.03	0.03
	Over 1.00 to 2.00 incl	0.05	0.05	0.05	0.05
	Over 2.00 to 5.30 incl	0.07	0.07	0.07	0.07
	Over 5.30 to 10.00 incl	0.10	0.10	0.10	0.10
Chromium	To 0.90 incl	0.03	0.04	0.04	0.05
	Over 0.90 to 2.10 incl	0.05	0.06	0.06	0.07
	Over 2.10 to 3.99	0.10	0.10	0.12	0.14
Molybdenum	To 0.20 incl	0.01	0.01	0.02	0.03
	Over 0.20 to 0.40 incl	0.02	0.03	0.03	0.04
	Over 0.40 to 1.15 incl	0.03	0.04	0.05	0.06
Tungsten	To 1.00 incl	0.04	0.05	0.05	0.06
	Over 1.00 to 4.00 incl	0.08	0.09	0.10	0.12
Vanadium	To 0.10 incl	0.01	0.01	0.01	0.01
	Over 0.10 to 0.25 incl	0.02	0.02	0.02	0.02
	Over 0.25 to 0.50 incl	0.03	0.03	0.03	0.03
	Min value specified, check under min limit	0.01	0.01	0.01	0.01

Element	Limit or Max of Specified Range, %	Variation, %, Over Max Limit or Under Min Limit Bars, Sheet, Strip, Tubing, and Semifinished Products to 0.0645 m ² (100 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products Over 0.0645 to 0.129 m ² (100 to 200 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products Over 0.129 to 0.258 m ² (200 to 400 in ²) incl	Variation, %, Over Max Limit or Under Min Limit Semifinished Products Over 0.258 to 0.516 m ² (400 to 800 in ²) incl
Aluminum	Up to 0.10 incl	0.03	—	—	—
	Over 0.10 to 0.20 incl	0.04	—	—	—
	Over 0.20 to 0.30 incl	0.05	—	—	—
	Over 0.30 to 0.80 incl	0.07	—	—	—
	Over 0.80 to 1.80 incl	0.10	—	—	—

Table 4 - Permissible variations from specified chemical ranges and limits for stainless steels (from ASTM A480/A480M)

Element	Limit or Max of Specified Range, %	Variation, %, Over Max Limit or Under Min Limit
Carbon	To 0.010 incl	0.002
	Over 0.010 to 0.030 incl	0.005
	Over 0.030 to 0.20 incl	0.01
	Over 0.20 to 0.60 incl	0.02
	Over 0.60 to 1.20 incl	0.03
Manganese	To 1.00 incl	0.03
	Over 1.00 to 3.00 incl	0.04
	Over 3.00 to 6.00 incl	0.05
	Over 6.00 to 10.00 incl	0.06
	Over 10.00 to 15.00 incl	0.10
	Over 15.00 to 20.00 incl	0.15
Phosphorus	To 0.040 incl	0.005
	Over 0.040 to 0.20 incl	0.010
Sulfur	To 0.040 incl	0.005
	Over 0.040 to 0.20 incl	0.010
	Over 0.20 to 0.50 incl	0.020
Silicon	To 1.00 incl	0.05
	Over 1.00 to 3.00 incl	0.10
	Over 3.00 to 7.00 incl	0.15

Element	Limit or Max of Specified Range, %	Variation, %, Over Max Limit or Under Min Limit
Chromium	Over 4.00 to 10.00 incl	0.10
	Over 10.00 to 15.00 incl	0.15
	Over 15.00 to 20.00 incl	0.20
	Over 20.00 to 30.00 incl	0.25
Nickel	To 1.00 incl	0.03
	Over 1.00 to 5.00 incl	0.07
	Over 5.00 to 10.00 incl	0.10
	Over 10.00 to 20.00 incl	0.15
	Over 20.00 to 30.00 incl	0.20
	Over 30.00 to 40.00 incl	0.25
	Over 40.00	0.30
Molybdenum	Over 0.20 to 0.60 incl	0.03
	Over 0.60 to 2.00 incl	0.05
	Over 2.00 to 8.00 incl	0.10
Titanium	To 1.00 incl	0.05
	Over 1.00 to 3.00 incl	0.07
Niobium ¹	To 1.50 incl	0.05
Tantalum	To 0.10 incl	0.02
Copper	To 0.5 incl	0.03
	Over 0.50 to 1.00 incl	0.05
	Over 1.00 to 3.00 incl	0.10
	Over 3.00 to 5.00 incl	0.15
	Over 5.00 to 10.00 incl	0.20
Cobalt ²	Over 0.05 to 0.50 incl	0.01
	Over 0.50 to 2.00 incl	0.02
	Over 2.00 to 5.00 incl	0.05
Aluminum	To 0.15 incl	-0.005, +0.01
	Over 0.15 to 0.50 incl	0.05
	Over 0.50 to 2.00 incl	0.10
Selenium	All ranges	0.03

Element	Limit or Max of Specified Range, %	Variation, %, Over Max Limit or Under Min Limit
Nitrogen	To 0.02 incl	0.005
	Over 0.02 to 0.19 incl	0.01
	Over 0.19 to 0.25 incl	0.02
	Over 0.25 to 0.35 incl	0.03
	Over 0.35 to 0.45 incl	0.04
	Over 0.45 to 0.55 incl	0.05
Tungsten	To 1.00 incl	0.03
	Over 1.00 to 2.00 incl	0.05
	Over 2.00 to 5.00 incl	0.07
	Over 5.00 to 10.00 incl	0.10
	Over 10.00 to 20.00 incl	0.15
Vanadium	To 0.50 incl	0.03
	Over 0.50 to 1.50 incl	0.05

¹ Niobium (Nb) and columbium (Cb) are considered interchangeable names.

² Product analysis limits for cobalt under 0.05% have not been established and the manufacturer should be consulted for those limits.

Table 5 - Product analysis tolerances for structural shapes and plates (from ASTM A6)

Element	Limit, or Max Specified Value, %	Tolerances, % Under Min Limit	Tolerances, % Over Max Limit
Carbon	To 0.15 incl	0.02	0.03
	Over 0.15 to 0.40 incl	0.03	0.04
	Over 0.40 to 0.75 incl	0.04	0.05
	Over 0.75	0.04	0.06
Manganese ¹	To 0.60 incl	0.05	0.06
	Over 0.60 to 0.90 incl	0.06	0.08
	Over 0.90 to 1.20 incl	0.08	0.10
	Over 1.20 to 1.35 incl	0.09	0.11
	Over 1.35 to 1.65 incl	0.09	0.12
	Over 1.65 to 1.95 incl	0.11	0.14
	Over 1.95	0.12	0.16
Phosphorus	To 0.04 incl	—	0.010
	Over 0.04 to 0.15 incl	—	NA ²
Sulfur	To 0.06 incl	—	0.010
	Over 0.06	NA ²	NA ²