



AEROSPACE MATERIAL SPECIFICATION

SAE MAM 2241D

Issued JAN 1983
Noncurrent MAR 2003

Superseding MAM 2241C

Tolerances, Metric
Corrosion and Heat Resistant Steel, Iron Alloy,
Titanium, and Titanium Alloy Bars and Wire

NONCURRENCY NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March, 2003. It is recommended, therefore, that this specification not be specified for new designs.

AMS 2241 covers the same requirements.

"NONCURRENT" refers to those materials which have been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs.

"NONCURRENT" specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of MAM2241D

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 Society of Automotive Engineers, Inc.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: custsvc@sae.org

SAE WEB ADDRESS: <http://www.sae.org>

1. SCOPE:

This specification covers established metric manufacturing tolerances applicable to corrosion and heat resistant steel, iron alloy, titanium, and titanium alloy bars and wire ordered to metric dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "excl" is used to apply only to the higher figure of the specified range.

1.1 AMS 2241 is the inch/pound version of this MAM.

2. DIAMETER, THICKNESS, AND WIDTH:**2.1 Cold Finished Bars:**

2.1.1 Rounds, Squares, Hexagons, and Octagons (See 2.1.3): See Table 1.

TABLE 1 - Diameter or Thickness Tolerances

Specified Diameter or Thickness Millimeters	Tolerance, Millimeter Plus and Minus (See 2.1.1)	Tolerance, Millimeter	
		Rounds	Minus Only (See 2.1.1.2) Squares, Hexagons, and Octagons
Over 12.50 to 25.00, excl 25.00	0.05 0.062	0.10	0.10
Over 25.00 to 37.50, excl 37.50 to 50.00, incl	0.026 0.08	0.15	0.15
Over 50.00 to 75.00, incl	0.08	0.20	
Over 75.00 to 100.00, incl	0.08	0.25	

2.1.1.1 Size tolerances for round bars are plus and minus as shown in Table 1. When required, however, they may be specified all plus and nothing minus, or all minus and nothing plus, or any combination of plus and minus, if the total spread in size tolerance for a specified size is not less than the total spread shown in Table 1.

2.1.1.2 For titanium and titanium alloys, the difference among the three measurements of the distance between opposite faces of hexagons shall be not greater than one-half the size tolerance and the difference among the measurements of the distance between opposite faces of octagons shall be not greater than the size tolerance.

2.1.2 Flats (See 2.1.3): See Table 2.

TABLE 2 - Thickness and Width Tolerances

Specified Width Millimeters	Thickness Tolerance, Millimeter Plus and Minus		Width Tolerance, Millimeter Plus and Minus
	3.00 to 6.00, incl	0.05	
Over 6.00 to 25.00, incl	0.05	0.05	
Over 25.00 to 50.00, incl	0.08	0.08	
Over 50.00 to 75.00, incl	0.10	0.10	
Over 75.00 to 115.00, incl	0.12	0.12	

2.1.3 If cold finished bars are ordered heat treated or heat treated and pickled after cold finishing, tolerances shall be double those of Table 1 and Table 2.

2.2 Cold Finished Wire:

2.2.1 Rounds, Squares, Hexagons, and Octagons (See 2.2.1.1): See Table 3.

TABLE 3 - Diameter of Thickness Tolerances

Specified Diameter or Thickness Millimeters	Tolerance, Millimeters Plus and Minus		Tolerance, Millimeter Minus Only (See 2.2.1.3) Hexagons and Octagons
	Rounds and Squares		
0.08 to 0.12, excl	0.002		-
0.12 to 0.20, excl	0.005		-
0.20 to 0.30, excl	0.008		-
0.30 to 0.60, excl	0.010 (See 2.2.1.2)		-
0.60 to 0.85, excl	0.012 (See 2.2.1.2)		-
0.85 to 1.10, excl	0.020		-
1.10 to 3.15, excl	0.02		-
3.15 to 7.80, excl	0.02	0.05	
7.80 to 12.50, excl	0.038	0.08	
12.50	0.05	0.10	

2.2.1.1 If cold finished wire is ordered heat treated or heat treated and pickled after cold finishing, tolerances shall be double those of Table 3 for nominal sizes 0.60 millimeters and over.

2.2.1.2 For titanium and titanium alloys, tolerances for these sizes are ± 0.019 millimeter.

2.2.1.3 For titanium and titanium alloys, the difference among the three measurements of the distance between opposite faces of hexagons shall be not greater than one-half the size tolerance and the difference among the four measurements of the distance between opposite faces of octagons shall be not greater than one-half the size tolerance.

2.2.1.4 Out-of-Round: Round wire shall not be out-of-round by more than one-half of the total tolerance shown in Table 3.

2.2.2 Flats: See Table 4.

TABLE 4 - Thickness Tolerances

Specified Thickness Millimeters	Tolerance, Millimeter Plus and Minus
Up to 0.70, excl	0.02
0.70 to 0.90, excl	0.038
0.90 to 4.75, excl	0.04

2.2.2.1 Width tolerances shall be ± 0.12 millimeter for specified widths 1.56 to 9.38 millimeters, exclusive.

2.3 Hot Finished Bars:

2.3.1 Hot Rolled:

2.3.1.1 Rounds and Squares: See Table 5. Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross section. Out-of-square is the difference in the two dimensions at the same cross section of a square bar, each dimension being the distance between opposite faces.

TABLE 5 - Diameter or Thickness Tolerances

Specified Diameter or Thickness Millimeters	Tolerance Millimeters Plus	Tolerance Millimeter Minus	Out-of-Round or Out-of-Square Millimeters
6.25 to 7.80, incl	0.12	0.12	0.20
Over 7.80 to 11.00, incl	0.15	0.15	0.22
Over 11.00 to 15.75, incl	0.18	0.18	0.25
Over 15.75 to 22.00, incl	0.20	0.20	0.30
Over 22.00 to 25.00, incl	0.22	0.22	0.32
Over 25.00 to 28.00, incl	0.25	0.25	0.38
Over 28.00 to 31.00, incl	0.28	0.28	0.40
Over 31.00 to 34.00, incl	0.30	0.30	0.45
Over 34.00 to 37.50, incl	0.35	0.35	0.52
Over 37.50 to 50.00, incl	0.40	0.40	0.58
Over 50.00 to 62.50, incl	0.80	0	0.58
Over 62.50 to 87.50, incl	1.20	0	0.88
Over 87.50 to 115.00, incl	1.60	0	1.15
Over 115.00 to 138.00, incl	2.00	0	1.45
Over 138.00 to 165.00, incl	3.15	0	1.75
Over 165.00 to 200.00, incl	3.90	0	2.12

2.3.1.2 Hexagons and Octagons: See Table 6.

TABLE 6 - Thickness Tolerances

Specified Thickness Millimeters	Tolerance Millimeters Plus and Minus	Maximum Difference 3 Measurements Hexagons Only Millimeters
6.25 to 12.50, incl	0.18	0.28
Over 12.50 to 25.00, incl	0.25	0.38
Over 25.00 to 37.50, incl	0.52	0.62
Over 37.50 to 50.00, incl	0.78	0.78
Over 50.00 to 62.50, incl	1.18	1.18
Over 62.50 to 87.50, incl	1.56	1.56

2.3.1.3 Flats: See Table 7 and Table 8.

TABLE 7 - Thickness Tolerances, Millimeters; For Thickness Ranges, Millimeters

Specified Width Millimeters	Over 3.10 to		Over 12.5 to		Over 25.00 to		Over 12.50, 25.00, 50.00, 100.00, 100.00, 150.00, 150.00, 200.00, 200.00, 250.00 to		Over 50.00 to 100.00, 100.00, 150.00, 150.00, 200.00, 200.00, 250.00 to		Over 100.00 to 150.00, 150.00, 200.00, 200.00, 250.00 to		Over 150.00 to 200.00, 200.00, 250.00 to		Over 200.00 to 250.00, 250.00 to	
	Inc.	Incl	Incl	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus
	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus	Plus
	and	and	and	Minus	Minus	Minus	Minus	Minus	Minus	Minus	Minus	Minus	Minus	Minus	Minus	Minus
Up to 25.00, incl	0.20	0.25	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Over 25.00 to 50.00, incl	0.30	0.38	0.78	-	-	-	-	-	-	-	-	-	-	-	-	-
Over 50.00 to 100.00, incl	0.38	0.50	0.78	1.55	0.78	-	-	-	-	-	-	-	-	-	-	-
Over 100.00 to 150.00, incl	0.38	0.50	0.78	1.55	0.78	2.32	1.55	-	-	-	-	-	-	-	-	-
Over 150.00 to 200.00, incl	0.40	0.62	0.78	1.55	0.78	2.32	1.55	3.12	3.12	3.12	3.12	3.90	-	-	-	-
Over 200.00 to 250.00, incl	0.52	0.78	0.78	1.55	0.78	2.32	1.55	3.12	3.12	3.12	3.90	-	-	-	-	-

TABLE 8 - Width Tolerances

Specified Width Millimeters	Tolerance, Millimeters		Tolerance, Millimeters	
	Plus	Minus	Plus	Minus
Up to 25.00, incl	0.38	0.38	0.38	0.38
Over 25.00 to 50.00, incl	0.78	0.78	0.78	0.78
Over 50.00 to 100.00, incl	1.55	0.78	1.55	0.78
Over 100.00 to 150.00, incl	2.32	1.55	2.32	1.55
Over 150.00 to 200.00, incl	3.12	3.90	3.12	3.90
Over 200.00 to 250.00, incl	3.90	4.68	-	-

2.3.2 Forged: Tolerances shall be as agreed upon by purchaser and vendor.

3. LENGTH:

Tolerances in Table 9 and Table 10 shall apply only when definite lengths are ordered.

3.1 Hot or Cold Finished Bars:

See Table 9.