



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



MAM 6415A

Issued JAN 1989
Revised JUN 1996

Superseding MAM 6415

STEEL, BARS, FORGINGS, AND TUBING
0.80Cr - 1.8Ni - 0.25Mo (0.38 - 0.43C) (SAE 4340)

UNS G43406

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, and forging stock procured in SI (Metric) units.

1.1.1 AMS 6415 is the inch/pound version of this MAM.

1.2 Application:

These products have been used typically for parts, 90 millimeters and under in nominal thickness at time of heat treatment, requiring a through-hardening steel capable of developing a minimum hardness of 40 HRC when properly hardened and tempered and also for parts of greater thickness but requiring proportionately lower hardness, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

MAM 6415A

SAE

MAM 6415A

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- MAM 2251 Tolerances, Metric, Low-Alloy Steel Bars
- MAM 2253 Tolerances, Metric, Carbon and Alloy Steel Tubing
- AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- MAM 2301 Cleanliness, Aircraft-Quality Steel, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
- AMS 2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
- AMS 2372 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings
- AS1182 Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing
- ARP1110 Minimizing Stress Corrosion Cracking in Wrought Forms of Steels and Corrosion Resistant Steels and Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM A 255 End-Quench Test for Hardenability of Steel
- ASTM A 370 Mechanical Testing of Steel Products
- ASTM E 112 Determining the Average Grain Size
- ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
- ASTM E 381 Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

- MIL-H-6875 Heat Treatment of Steel, Process for
- MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

MAM 6415A

SAE

MAM 6415A

TABLE 1 - Composition

Element	min	max
Carbon	0.38	0.43
Manganese	0.65	0.85
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.70	0.90
Nickel	1.65	2.00
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370.

3.2.1 Bars:

3.2.1.1 Bars 12.50 Millimeters and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 862 MPa or hardness not higher than 27 HRC, or equivalent (See 8.2).

3.2.1.2 Bars Over 12.50 Millimeters in Nominal Diameter or Distance Between Parallel Sides: Hot finished and annealed having hardness not higher than 235 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 255 HB, or equivalent (See 8.2).

3.2.2 Forgings: Normalized and tempered in accordance with MIL-H-6875 to a hardness not higher than 269 HB, or equivalent (See 8.2).

3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 25 HRC, or equivalent, except that tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent (See 8.2).

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

MAM 6415A

SAE

MAM 6415A

- 3.3.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds or tubes, and forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Except as specified in 3.3.1.1, porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure Limits

Cross-Sectional Area Square Centimeters	Macrographs
Up to 230, incl	S2 - R1 - C2
Over 230 to 645, incl	S2 - R2 - C3

- 3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.
- 3.3.2 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112 (See 8.3).
- 3.3.3 Hardenability: Shall be J53=17 mm, minimum and J50=32 mm, minimum, determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalized at $870\text{ }^{\circ}\text{C} \pm 15$ and the test specimen austenitized at $845\text{ }^{\circ}\text{C} \pm 15$.
- 3.3.4 Decarburization:
- 3.3.4.1 Bars and tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.
- 3.3.4.2 Allowable decarburization of bars, billets, and tube rounds ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.3.4.3 Decarburization of bars to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 3.

MAM 6415A

SAE

MAM 6415A

TABLE 3 - Maximum Decarburization

Nominal Diameter or Distance Between Parallel Sides Millimeters		Depth of Decarburization Millimeters
Up to	9.50, incl	0.25
Over	9.50 to 12.50, incl	0.30
Over	12.50 to 15.65, incl	0.35
Over	15.65 to 25.00, incl	0.40
Over	25.00 to 37.50, incl	0.50
Over	37.50 to 50.00, incl	0.60
Over	50.00 to 62.50, incl	0.75
Over	62.50 to 75.00, incl	0.90
Over	75.00 to 100.00, incl	1.15

- 3.3.4.4 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 4.

TABLE 4 - Maximum Decarburization

Nominal Wall Thickness Millimeters		Depth ID Millimeter	Depth OD Millimeter
Up to	2.75, incl	0.20	0.35
Over	2.75 to 5.00, incl	0.25	0.50
Over	5.00 to 10.00, incl	0.30	0.60
Over	10.00 to 15.00, incl	0.35	0.75
Over	15.00 to 25.00, incl	0.40	0.90
Over	25.00	0.50	1.00

- 3.3.4.5 Decarburization shall be measured by the microscopic method or by the HR30N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization thereon.
- 3.3.4.5.1 (R) When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.13 millimeter and the width is 1.65 millimeters or less.

MAM 6415A

SAE

MAM 6415A

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Steel shall be aircraft-quality conforming to MAM 2301.

3.4.2 Bars and mechanical tubing ordered hot rolled or cold drawn, or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5 Tolerances:

Shall be as follows:

3.5.1 Bars: In accordance with MAM 2251.

3.5.2 Mechanical Tubing: In accordance with MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), condition (3.2), macrostructure (3.3.1), average grain size (3.3.2), hardenability (3.3.3), decarburization (3.3.4), frequency-severity cleanliness rating (3.4.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Grain flow of die forgings (3.4.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing: (R)

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

4.3.2 Forgings: In accordance with AMS 2372.