



UL 565

STANDARD FOR SAFETY

Liquid-Level Gauges for Anhydrous Ammonia and LP-Gas

ULNORM.COM : Click to view the full PDF of UL 565 2018

ULNORM.COM : Click to view the full PDF of UL 565 2018

UL Standard for Safety for Liquid-Level Gauges for Anhydrous Ammonia and LP-Gas, UL 565

Sixth Edition, Dated September 13, 2013

Summary of Topics

This revision of ANSI/UL 565 is being issued to reflect the following:

1. Revisions to the 10-day moist ammonia-air stress cracking test

Text that has been changed in any manner or impacted by UL's electronic publishing system is marked with a vertical line in the margin. Changes in requirements are marked with a vertical line in the margin and are followed by an effective date note indicating the date of publication or the date on which the changed requirement becomes effective.

The revised requirements are substantially in accordance with Proposal(s) on this subject dated January 19, 2018.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

Users of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgment (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

No Text on This Page

ULNORM.COM : Click to view the full PDF of UL 565 2018

SEPTEMBER 13, 2013
(Title Page Reprinted: February 23, 2018)



ANSI/UL 565-2018

1

UL 565

Standard for Liquid-Level Gauges for Anhydrous Ammonia and LP-Gas

Prior to the sixth edition, the standard was titled Liquid-Level Gauges and Indicators for Anhydrous Ammonia and LP-Gas.

First Edition – November, 1958
Second Edition – January, 1973
Third Edition – November, 1986
Fourth Edition – December, 1993
Fifth Edition – September, 1998

Sixth Edition

September 13, 2013

This ANSI/UL Standard for Safety consists of the Sixth Edition including revisions through February 23, 2018.

The most recent designation of ANSI/UL 565 as an American National Standard (ANSI) occurred on February 22, 2018. ANSI approval for a standard does not include the Cover Page, Transmittal Pages, and Title Page.

Comments or proposals for revisions on any part of the Standard may be submitted to UL at any time. Proposals should be submitted via a Proposal Request in UL's On-Line Collaborative Standards Development System (CSDS) at <https://csds.ul.com>.

UL's Standards for Safety are copyrighted by UL. Neither a printed nor electronic copy of a Standard should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

COPYRIGHT © 2018 UNDERWRITERS LABORATORIES INC.

No Text on This Page

ULNORM.COM : Click to view the full PDF of UL 565 2018

CONTENTS

INTRODUCTION

1 Scope	4
2 General	4
2.1 Components	4
2.2 Units of measurement	5
2.3 Undated references	5
2.4 Pressure and temperature rating	5
3 Glossary	5

CONSTRUCTION

4 Assembly	6
5 Materials	7
6 Bodies	9
7 Springs	9
8 Floats	9

PERFORMANCE

9 General	9
10 External Leakage Test	10
11 Hydrostatic Strength Test	10
12 Endurance Test	10
13 Float Crush Test	10A
14 Moist Ammonia-Air Stress Cracking Test	10A

MANUFACTURING AND PRODUCTION TESTS

15 General	10B
------------------	-----

MARKING

16 General	10B
------------------	-----

APPENDIX A

Standards for Components.....	A1
-------------------------------	----

INTRODUCTION

1 Scope

1.1 These requirements cover liquid-level gauges for anhydrous ammonia and liquefied petroleum gas (LP-Gas) for use with pressure vessels in nonrefrigerated systems in installations covered by the following American National Standards and others:

- a) Compressed Gas Association, CGA G-2.1.
- b) Liquefied Petroleum Gas Code, NFPA 58.
- c) Storage and Handling of Liquefied Petroleum Gases at Utility Plants, ANSI/NFPA 59.

1.2 These requirements cover designs of gauges that require the release of liquid or gas phases of the contained fluid in order to function and gauges that do not require the release of liquid or gas phases of the contained fluid to function.

2 General

2.1 Components

2.1.1 Except as indicated in 2.1.2, a component of a product covered by this standard shall comply with the requirements for that component. See Appendix A for a list of standards covering components generally used in the products covered by this standard.

2.1.2 A component is not required to comply with a specific requirement that:

- a) Involves a feature or characteristic not required in the application of the component in the product covered by this standard, or
- b) Is superseded by a requirement in this standard.

2.1.3 A component shall be used in accordance with its rating established for the intended conditions of use.

2.1.4 Specific components are incomplete in construction features or restricted in performance capabilities. Such components are intended for use only under limited conditions, such as certain temperatures not exceeding specified limits, and shall be used only under those specific conditions.

2.2 Units of measurement

2.2.1 Values stated without parentheses are the requirement. Values in parentheses are explanatory or approximate information.

2.3 Undated references

2.3.1 Any undated reference to a code or standard appearing in the requirements of this standard shall be interpreted as referring to the latest edition of that code or standard.

2.4 Pressure and temperature rating

2.4.1 The rated service-pressure of a gauging device covered by these requirements shall not be less than 250 psig (1.7 MPa gauge).

2.4.2 Gauging devices covered by these requirements are intended for use at ambient temperatures within the range of minus 40°C – 55°C (minus 40°F – 55°F).

3 Glossary

3.1 For the purpose of this standard the following definitions apply.

3.2 **FIXED LIQUID LEVEL GAUGE** – A liquid level indicator that uses a positive shutoff vent valve to indicate that the liquid level in a container being filled has reached the point at which the indicator communicates with the liquid level in the container.

Reproduced with permission from NFPA 58-2011, *LP-Gas Code Handbook*, Copyright ©2010, National Fire Protection Association

3.3 **LIQUEFIED PETROLEUM GAS (LP-GAS OR LPG)** – Any material having a vapor pressure not exceeding that allowed for commercial propane that is composed predominantly of the following hydrocarbons, either by themselves (excluding propylene) or as mixtures: propane, propylene, butane (normal butane or isobutane) and butylenes.

3.4 **MAGNETIC-FLOAT GAUGE** – A type of variable liquid level gauge that incorporates a float that rests on the liquid level, which is connected to a series of gears and linkages that move in relation to the liquid level. The dial is connected to the gears and linkages through magnets on either side of the enclosure so no leakage occurs if there is a failure of the linkage mechanism. This type of gauge does not release contained fluid to atmosphere in order to function.

3.5 **ROTARY GAUGE** – A type of variable liquid level gauge that indicates the liquid level on a dial gauge installed on an ASME container by manually rotating an open ended tube inside the container, which is connected to a positive shutoff vent valve.

Reproduced with permission from NFPA 58-2011, *LP-Gas Code Handbook*, Copyright ©2010, National Fire Protection Association

3.6 **SLIP TUBE GAUGE** – A variable liquid level gauge in which a small positive shutoff valve is located at the outside end of a straight tube that is installed vertically within a container.

Reproduced with permission from NFPA 58-2011, *LP-Gas Code Handbook*, Copyright ©2010, National Fire Protection Association

3.7 VARIABLE LIQUID LEVEL GAUGE – A device that indicates the liquid level in a container throughout a range of levels.

Reproduced with permission from NFPA 58-2011, *LP-Gas Code Handbook*, Copyright ©2010, National Fire Protection Association

3.8 VENT VALVE – A type of manual shutoff valve that has a controlled orifice. Gauges that employ a vent valve release contained fluid to atmosphere to function.

CONSTRUCTION

4 Assembly

4.1 A gauge, when not assembled by the manufacturer as a unit, shall be arranged in as few subassemblies as practical; and shall be capable of being installed as a final assembly without alteration, other than for adjustment in the length of a gauging tube.

4.2 When a design requires the use of tubing, tubing fittings, pipe fittings, gaskets, bolts, cap screws, and the like, for making a proper installation, such parts shall be furnished by the manufacturer with each gauge when shipped.

4.3 The construction shall be such that parts can be readily reassembled in their intended manner after being dismantled to the extent needed for installation and normal care.

4.4 Convenient means shall be provided for the purpose of making any necessary field adjustment.

4.5 A brazing material used for joining fluid confining parts of a gauge for LP-Gas shall have a melting point (solidus temperature) not less than 538°C (1000°F). Brazing shall not be used on assemblies for anhydrous ammonia.

4.6 A dial of a magnetic-float or of a rotary-tube type gauge intended to be installed on a container greater than 1200 gallons for use with LP-Gas, and which is intended to be used for filling in accordance with the Liquefied Petroleum Gas Code, NFPA 58, shall be marked so that the maximum liquid level for butane, for a 50-50 butane-propane mixture, and for propane is readily determinable at temperatures between minus 7 and 46°C (20 and 115°F). Markings shall be in increments of not more than 11°C (20°F).

Exception: If the marked temperature range does not include minus 7 and 46°C (20 and 115°F), the gauge dial shall be marked in accordance with 16.4.

4.7 A dial of a gauge intended to be installed on a container greater than 1200 gallons that is not to be used for filling shall be marked in accordance with 16.5.

4.8 A dial of a magnetic-float or of a rotary-tube type gauge intended to be installed on ASME containers for use with anhydrous ammonia shall be marked so that the maximum liquid level for anhydrous ammonia is readily determinable at temperatures between minus 7 and 38°C (20 and 100°F). Markings shall be in increments of not more than 11°C (20°F).

Exception: If the marked temperature range does not include minus 7 and 38°C (20 and 100°F), the gauge dial shall be marked in accordance with 16.4.

4.9 A dial of a magnetic-float or of a rotary-tube type gauge for use with LP-Gas shall be marked to indicate whether it is for use with cylindrical or spherical containers and whether it is for use in aboveground or underground service.

4.10 A dial of a magnetic-float or of a rotary-tube type gauge for use only in LP-Gas aboveground containers of over 1200 gallons (4542 L) water capacity shall be so marked.

4.11 Dial markings shall be legible and shall not be readily discolored or obliterated by weathering.

4.12 A gauge, other than for farm use as mentioned in 4.13, that requires the release of the contained fluid to the atmosphere to function, such as those of the rotary-tube, slip-tube, fixed-tube, and vent-valve types, shall be constructed so that the controlling orifice is not larger than a No. 54 (0.055-inch diameter) drill size.

4.13 A fixed-tube or a vent-valve gauge that is intended for mounting on a container for anhydrous ammonia used solely on farm equipment for field application of ammonia, is permitted to be constructed with a controlling orifice larger than that indicated in 4.12, but not larger than 7/16-inch diameter. Such a device shall be marked with the size of the opening.

4.14 A gauging tube of a slip-tube type of liquid-level gauge shall be constructed with a substantially secured stop on its lower end to prevent the tube from being withdrawn completely from the body of the gauge or forced out by container pressure.

5 Materials

5.1 Fluid confining parts of a gauge, or its operating parts, the failure of which might result in leakage, shall have the strength and durability necessary to perform their intended function.

5.2 A part in contact with the fluid to be handled shall be resistant to the action of such fluid.

5.3 Only iron, steel, and certain nonferrous alloys that are suitable for ammonia service, are to be used in contact with anhydrous ammonia. Ammonia containing minute quantities of water will react rapidly with copper, zinc, and many alloys, especially those of copper base.

5.4 Nonductible cast iron (gray iron) shall not be used for bodies or closures in contact with anhydrous ammonia and LP-Gas.

5.5 A synthetic rubber part in contact with one of the fluids indicated in Table 5.1 shall not show excessive volume change or loss of weight, when considered on the basis of its intended function, following immersion for 70 hours in the specified test liquid.

Table 5.1
Test liquids for synthetic rubber materials

Fluid in contact with part	Test liquid
LP-Gas	n-Hexane
Anhydrous ammonia	Liquid anhydrous ammonia

5.6 A change in volume of not more than 25 percent swelling or 1 percent shrinkage, and a weight loss (extraction) of not more than 10 percent is considered as indicating compliance with 5.5.

5.7 A part made of synthetic rubber that is affected by aging shall not crack or show visible evidence of deterioration following exposure in an air oven for 70 hours at a temperature of $100 \pm 2^{\circ}\text{C}$ ($212 \pm 3.6^{\circ}\text{F}$).

5.8 When corrosion of a ferrous part interferes with the intended function of a gauge, the part shall be provided with a corrosion-resistant protective coating.

5.9 A protective coating shall provide resistance against corrosion to a degree not less than that provided by the protective coatings indicated in 5.10.

5.10 Cadmium plating shall be minimum 0.0003 inch (0.008 mm) thick and zinc plating shall be minimum 0.0005 inch (0.013 mm) thick.

Exception: In cases where threads constitute the major portion of the area, the thickness of the cadmium or the zinc plating shall be minimum 0.00015 inch (0.0038 mm) thick.

5.11 A part made of drawn brass or machined from brass rod shall withstand, without cracking, a 10-Day Moist Ammonia-Air Stress Cracking Test for copper and copper alloys. See 10-Day Moist Ammonia-Air Stress Cracking Test, Section 14.

5.12 A glass or a plastic part shall not be used in the construction of a gauge when breakage or destruction of the part will result in the escape of fluid from the tank to which it is attached.

5.13 A glass part, where permitted, shall be protected against breakage and shall withstand a sudden temperature reduction of 56°C (100°F) from not more than 100°C (212°F) without the development of cracks.

5.14 A plastic part, where permitted, shall be resistant to deterioration and distortion under conditions of intended service.

6 Bodies

6.1 A body or a part designed to be threaded into an opening in a container or designed for connection of piping shall have the required strength to withstand the normal stresses of installation and shall be constructed with a section to serve as a wrench grip.

6.2 A flange or other part of a body designed to be clamped in place when the gauge is installed shall have the required strength to withstand the stresses imposed by tightening the clamping screws or bolts.

6.3 Pipe threads shall be in accordance with the Standard for Pipe Threads, General Purpose (Inch), ANSI/ASME B1.20.1.

Exception: Gauges intended for use in installations where pipe fittings incorporate other than NPT type threads shall be permitted to be provided with pipe threads complying with a national pipe thread standard compatible with those fittings. The pipe thread type shall be identified in accordance with 16.8.

7 Springs

7.1 A spring shall be guided and arranged to reduce binding, buckling, or other interference with its free movement. When necessary, both ends of a spring shall be closed and squared.

8 Floats

8.1 A float designed to actuate a gauging mechanism shall have a buoyancy not less than 50 percent greater than that required to operate the mechanism, unless a counterbalanced arrangement is used.

8.2 A hollow float shall withstand an external crushing pressure of not less than 750 psig (5.2 MPa).

8.3 A float shall be secured to its corresponding lever, rod, or other part of the mechanism by a method that prevents the float from becoming detached under service conditions.

PERFORMANCE

9 General

9.1 Representative samples of each size and specific design of a gauge are to be subjected to the tests described in these requirements. Additional samples of internal parts, such as parts made of nonmetallic materials, may be required for separate tests.

9.2 A leakage test on a gauge is to use a source of aerostatic pressure such as air, nitrogen, or carbon-dioxide gas. A hydrostatic strength test is not prohibited from using water for developing the required pressure. All pressures are to be maintained 1 minute.

9.3 For the External Leakage and Hydrostatic Strength Tests in Sections 10 and 11, a positive shutoff valve and a pressure measuring device shall be installed in the pressure supply piping between the shutoff valve and the product under test.

9.4 Pressure measuring devices shall be calibrated over the range that it is used. The test pressure measured shall be not less than 20 percent nor more than 80 percent of the full-scale reading of the device.

Exception: The test pressure is allowed to be less than 20 percent or more than 80 percent of the full-scale reading of the measuring device, when calibration indicates that there is no loss of accuracy in the measured value.

10 External Leakage Test

10.1 A liquid-level gauge shall withstand, without leakage, an internal aerostatic pressure of 375 psig (2.6 MPa), or 1-1/2 times the rated service pressure, whichever is higher. The pressure is applied with the vent valve, if provided, in the closed position.

11 Hydrostatic Strength Test

11.1 A liquid-level gauge, exclusive of any float used therein, shall withstand, without rupture or permanent distortion, an internal hydrostatic pressure of 1250 psig (8.6 MPa), or 5 times the rated service pressure, whichever is greater.

11.2 Samples of gauges previously subjected to the External Leakage Test, Section 10, are to be connected to a source of hydrostatic pressure.

12 Endurance Test

12.1 A variable liquid-level gauge that will permit the escape of vapor or liquid, in the event of failure of the gauging gears, linkage, or other mechanism, shall withstand 25,000 complete cycles of operation without failure or excessive wear of parts. Following the Endurance Test, the test gauge shall comply with the test requirement in External Leakage Test, Section 10.

12.2 A gauge that incorporates a vent valve shall withstand 1500 cycles of opening and closing of the vent valve seat disc with the main knob, handwheel, or stem assembly initially in the closed position and 100 psig aerostatic pressure applied to the valve inlet. The test is to be conducted manually and with a closing torque sufficient to stop air flow.

13 Float Crush Test

13.1 A hollow float shall withstand, without distortion, an external pressure of 750 psig (5.2 MPa).

13.2 Two samples of a hollow float are to be subjected to this test. Each float is to be inserted into a vessel of appropriate size and strength, that may be constructed of pipe and pipe fittings. The vessel is to be connected to a source of hydrostatic pressure. A pressure gauge having a range as described in 9.3, is to be installed in the pressure supply piping. The vessel is to be completely filled with liquid to expel all air. The pressure is then to be slowly increased to 750 psig (5.2 MPa).

13.3 Subsequent to the test, the floats are to be removed from the vessel and examined for evidence of distortion.

14 Moist Ammonia-Air Stress Cracking Test

14 revised February 23, 2018

14.1 After being subjected to the conditions described in 14.2 – 14.3, a pressure confining brass part containing more than 15 percent zinc shall:

- a) Show no evidence of cracking, delamination, or degradation; or
- b) Perform as intended when tested as described in 14.4.

14.2 One test sample of each size is to be subjected to the physical stresses normally imposed on or within a part as the result of assembly with other components. Samples with female tapered pipe threads, intended to be used for installing the product in the field, are to have the threads engaged and tightened to the torque specified in Table 14.1. Samples with female threads other than tapered pipe threads shall be torqued as specified by the manufacturer. Polytetrafluoroethylene (PTFE) tape or pipe compound is not to be used on any threads. Samples with male threads are evaluated in "as-received" condition.

14.2 revised February 23, 2018

14.3 The samples are then to be tested in accordance with Apparatus, Section 6, Reagents and Materials, Section 7, Test Media, Section 8, Test Sample Preparation (9.3 – 9.4), Test Procedure (10.1 – 10.4) of the Standard Test Method for Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys, ASTM B858-06, except the pH level of the test solution shall be High 10.5 $\pm$ 0.1 and the exposure temperature shall be 25 $\pm$ 1°C.

14.3 revised February 23, 2018

14.4 After the exposure period, the samples are to be examined for cracks or other signs of stress corrosion using a microscope having a magnification of 25X. Parts exhibiting degradation as indicated in 14.1 (a), as a result of the test exposure described in 14.2 and 14.3 shall be subjected to and comply with the Hydrostatic Strength Test Section 11.

14.4 revised February 23, 2018

Table 14.1
Torque requirements for threaded connections

Nominal thread size, inches	Torque,	
	pound-inches	(N·m)
1	1200	135.6
1-1/4	1450	163.8
1-1/2	1550	175.1
2	1650	186.4
2-1/2	1750	197.7
3	1800	203.4

MANUFACTURING AND PRODUCTION TESTS

15 General

15.1 The manufacturer shall provide the necessary production control, inspection, and tests of each gauge to determine that it is in proper operating condition and free from defects that may impair its serviceability.

15.2 Gauges that require the release of controlled fluid to atmosphere shall be tested and shown to be free from leakage at all joints, including the seat, using aerostatic pressure at the rated service pressure. In lieu of testing with aerostatic pressure, leakage tests are permitted to be conducted with a hydrostatic pressure at 1-1/2 times the rated service pressure.

MARKING

16 General

16.1 A gauge shall be marked with the following information:

- a) The manufacturer's or vendor's identification.
- b) A distinctive catalog number or equivalent identification to specifically identify the product.
- c) The fluid service, or services, for which the gauge is designed, such as "LPG" for liquefied petroleum gas, and/or "A-A" or "NH₃" for anhydrous ammonia.

16.2 The fluid service marking specified in 16.1(c) is not required if the manufacturer's or vendor's catalog and the catalog designation marked on the product individuates the service for which the gauge is intended.

16.3 The dials of magnetic-float type and rotary-tube type gauges shall be marked as specified in 4.6 – 4.10 and 4.13.

16.4 When a gauging device does not have the complete temperature range as required by 4.6 for LP-Gas use or 4.7 for anhydrous ammonia use, the dial shall include a cautionary statement that the container shall not be filled beyond the temperature range provided on the dial.

16.5 When a gauging device is for use on containers greater than 1200 gallons and does not include the temperature filling correction factors, the dial shall be marked that the gauge shall not be used for filling.

16.6 Markings shall be legible and of a permanent nature, as afforded by stamping or molding in a casting, or by a metal or decalcomania transfer nameplate.

Exception: The marking required by 16.8 is not required to be permanent.

16.7 When a manufacturer produces gauges at more than one factory, each gauge shall have a distinctive marking to identify it as the product of a particular factory.

ULNORM.COM : Click to view the full PDF of UL 565 2018

No Text on This Page

ULNORM.COM : Click to view the full PDF of UL 565 2018